

667702KI Special Mirror Silver Screen Ink is a solvent-based ink for printing second surface on transparent polycarbonate film. The ink film exhibits a mirror-like reflective surface when viewed through the top or first surface of the polycarbonate film. Adhesion of the ink to substrates other than polycarbonate must be tested prior to any production run. The Mirror Silver Ink may not be compatible with laminating adhesives.

The thoroughly dried ink film may be overprinted with 9700 Series, 1500 Series or 1700 Series inks for further protection. Over-printing the mirror ink with other ink systems is not recommended.

**SUBSTRATES** Polycarbonate

## USER INFORMATION

*While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. See full disclaimer at the end of the document.*

**MESH** 305 - 380 threads per inch (120 - 150 threads per centimeter) monofilament polyester mesh for most applications

**STENCIL** Solvent resistant direct emulsions and capillary films

**SQUEEGEE** 70 - 80 durometer polyurethane squeegee

**COVERAGE** 2500 - 3500 square feet (232 - 325 square meters) per gallon depending upon ink deposit

**PRINTING** The 667702KI Special Mirror Silver ink is formulated to be press ready. Add only enough ink to the screen to be able to print for 5-10 minutes. Add additional ink in small increments throughout the print run to maintain screen stability. Thoroughly mix the inks prior to printing. The ink must be mixed at low shear.

Maintain ink temperatures at 65° - 90° F (18° - 32° C) for optimum print drying performance. Lower temperatures increase the ink viscosity, impairing both flow and drying. Elevated temperatures lower the ink viscosity, reducing print definition, film thickness and opacity.

Pretest to determine optimum printing performance for a particular set of ink, substrate, screen, press, and drying variables/conditions.

**DRYING** 667702KI ink dries by solvent evaporation. The ink may be dried at room temperature or dried in a 140°F (60°C) oven for at least 15 minutes. Drying at higher temperatures may affect the mirror-like appearance. The ink must be thoroughly dried for optimal properties. Due to varying ink deposits and production equipment, it is recommended that the printer evaluate the drying time and temperature that will allow the maximum reflectance for the specific application. Good air circulation is necessary to remove the vaporized solvents.

**CLEAR / VARNISHES** Overprint Clears: the following overprint clear inks may be printed over a thoroughly dried 667702KI ink film: 9727, 1527 or 1727.

**CLEAN UP** Screen Wash (Prior to Reclaim): Use IMS201 Premium Graphic Screen Wash.  
Press Wash (On Press): Use IMS301 Premium Graphic Press Wash.

**STORAGE** Store tightly covered at temperatures between 65° - 90° F (18° - 32° C). Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink.

### GENERAL INFORMATION

**INK HANDLING** All personnel mixing and handling this product must wear gloves and eye protection. Clean up spills immediately. If ink does come in contact with skin, wipe ink off with a clean, dry, absorbent cloth (do not use solvent or thinner). Wash the affected area with soap and water. Consult the 667702KI Material Safety Data Sheet for further instructions and warnings.

### PRODUCT OFFERING

**COLOR CARD MATERIALS** The following is a list of screen printed samples available.  
*Special Effects Color Card:* shows the 667702KI Special Mirror Silver Ink, Metallic, Pearlescent, Interference, and Multi-Chromatic effects mixed with clear

**PACKAGING** 667702KI is available in quart and gallon containers.

**PACKAGING** Cleaners are available in 1-gallon, 5-gallon and 55-gallon containers.

Stock Number	Clean Up
IMS201	Premium Graphic Screen Wash
IMS301	Premium Graphic Press Wash

*Nazdar<sup>®</sup> stands behind the quality of this product. Nazdar<sup>®</sup> cannot, however, guarantee the finished results because Nazdar<sup>®</sup> exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar<sup>®</sup>.*

Based on information from our raw material suppliers, this product is formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

Nazdar Worldwide Headquarters  
8501 Hedge Lane Terrace, Shawnee, KS 66227-3290 USA  
Toll Free: 866.340.3579 or Tel: 913.422.1888 Fax: 913.422.2296  
e-mail: [custserv@nazdar.com](mailto:custserv@nazdar.com)

Nazdar Limited  
Barton Road, Heaton Mersey, Stockport, England SK4 3EG  
Tel: + (44) 0.161.442.2111 Fax: + (44) 0.161.442.2001  
e-mail: [technicalservicesuk@nazdar.com](mailto:technicalservicesuk@nazdar.com)

<http://www.nazdar.com>