

Avery Dennison® UVTS-NazDar Ultraviolet Curable Printing Inks

Instructional Bulletin 8.38
Revised 08/2003

General Processing Guidelines

Substrate/Ink Compatibility

Avery Dennison UVTS-NazDar Ink is a one-component, UV curable ink system. Only Avery Dennison Reflective Sheeting, manufactured by Avery Dennison Corporation and approved for use in the traffic signage market is warranted for use with Avery Dennison UVTS-NazDar inks. UVTS-NazDar ink and required overprint clear or Avery Dennison OL-1000 Premium Anti-Graffiti Overlaminant is warranted for 10 years on T-6500 and T-7500 MVP (including fluorescent colors) reflective sheeting.

Substrate Conditioning

For best results, sheet stock should be allowed to stabilize under shop humidity and temperature conditions for 24 hours before a run is started. Refer to IB # 8.00 for more information.

Ink Preparation

All inks arrive press ready-to-use. All ink must be mixed with a high-speed mixer for 10 minutes before use.

Since Avery Dennison UVTS-NazDar Ink contains no solvents, there will be no evaporation during the course of the day or premature drying in the screen. The use of thinner / retarder is not required in the UVTS-NazDar Ink system.

Use only dark polyethylene plastic containers for mixing and storing. Keep containers tightly closed when not in use. Allow at least 10% airspace between the surface of the ink and the container lid. This air pocket extends the shelf life of the ink.

The UVTS-NazDar Ink warranty provides for five (5) years of outdoor durability when creating custom blends using standard traffic colors and Overprint Clear. Custom color matches made with additional components (other than standard traffic or mixing colors) are not warranted.

Product Color Range:

Yellow
Black
Orange
Blue
Green
Stop Sign Red
Brown
Overprint Clear
Mixing Clear
Screen Wash

UVTS-NazDar Printing Inks continued...

Mesh Recommendations

Avery Dennison UVTS-NazDar Inks offer a full range of traffic colors. Each pigment has been carefully selected to provide brilliantly clean transparent traffic colors with outstanding reflectivity when printed on Avery Dennison Reflective Sheeting. UVTS-NazDar Ink formulations have been matched to meet ASTM D 4956 color and reflectivity requirements when printed through a 305 (120cm) monofilament polyester (34 μ thread diameter) with 18-24 N/cm mesh tension mesh screen. Reflectivity on Avery Dennison Reflective sheeting screened with UVTS-NazDar Ink is warranted to achieve 70% of the ASTM value for the corresponding color.

Squeegee Selection

A medium -hard (70-90) durometer polyurethane squeegee blade is recommended. A sharp squeegee with the proper amount of pressure is required for optimum print resolution on all applications. Slight imperfections in the squeegee will be readily visible in the quality of the print. Thus, the condition of the squeegee and proper squeegee maintenance are a must. The squeegee blade must also be positioned at the correct angle to assure proper ink transfer.

Press Selection

To ensure consistent, reproducible color and reflectivity throughout the entire printing run, a fully or semi-automatic press is recommended. Care must be taken to ensure other printing variables, such as screen tension, mesh selection, etc., are consistent with the recommendations presented in this process guide.

Squeegee Technique

Most squeegee related problems are created by applying too much squeegee pressure. Any time the squeegee has enough pressure applied to bend the blade or severely change the angle, the proper "cutting edge" of the blade will be lost.

The lower the durometer of the squeegee, the more prone it will be to distortion from excess pressure. To mitigate this issue, a 70-90 durometer squeegee is recommended. The 70-90 durometer surface will contact the ink and screen to allow proper ink deposition and reduce screen wear from excessive abrasion.

Caution should also be exercised to ensure the screen frame is sufficiently larger than the print area. If the squeegee edge is too close to the frame, the screen will not stretch properly and uniformly during printing. This will cause the outside edges of the squeegee to bend with the pressure required to maintain substrate contact. The end result will be poor print quality.

Use of a Flood Stroke

Most screen printing mechanics require the use of a flood coat prior to the print (squeegee) stroke to assure consistency in color development and print resolution. At the proper printing viscosity, Avery Dennison UVTS Universal inks will have excellent flow characteristics; therefore, a heavy flood will significantly add to the amount of ink deposited resulting in poor reflectivity and color. **To prevent excess ink deposit a tight or minimal ink flood is recommended with little or no**

UVTS-NazDar Printing Inks continued...

time between flood and print strokes. For an automatic or semi-automatic press, the flood / print mode is recommended. Too much flood will smear small printed copy. A heavy flood coat will result in printing up to 50% more ink through the mesh, which will adversely affect color and reflectivity.

Curing

Assuming proper printed ink film thickness, Avery Dennison UVTS-NazDar Inks are formulated to cure when exposed to a focused, medium pressure mercury vapor lamp set at 300 watts per inch at a belt speed of 30-50 ft/min. Typically, 250-300 mJ/cm² can be obtained using the above curing recommendations. If the required level of energy output is not attainable at the stated conditions, it is recommended that the unit is inspected and the UV bulbs are cleaned to maximize energy output. If problems persist, please contact the equipment manufacturer. **NOTE: Clearcoat requires 250 to 300 mJ/cm² for complete cure** and can be printed or rollercoated.

It is important to keep the surface temperature of the sheeting under 110°F when curing UV inks. The routine use of some type of temperature indicator placed directly on the surface of the sheeting will allow you to properly check actual temperatures reached in the curing cycle.

Ink/Clear Coat Adhesion Test

After all adjustments to the printing press have been made, print a sample on the production sheeting. Place the printed sign onto the belt and pass through the UV curing unit. The curing unit should be adjusted and set to the initial energy setting recommended in this bulletin, under the section Curing.

Test the ink adhesion on the printed sign every 4" across the bulb width by scratching the surface with a dime and conducting a cross-cut test (as outlined in ASTM D3559 Method B). It is recommended that Scotch #610 tape be used for this test. The tape should remain on the sign for 60 seconds and then be removed with a quick pull at a 90 degree angle to the sign.

If the ink can't be scratched off with a coin or removed with the tape then proceed with the production run. However, if the ink can be scratched or removed from the sign then the ink is not properly cured. In this case, the UV cure unit settings need to be adjusted and the above test repeated.

Adhesion testing also needs to be evaluated for the required clear coat print over the ink color. The above guidelines need to be repeated for proper testing of the clear coat printed over the top of the properly cured color print. If poor adhesion continues please contact an Avery Dennison representative for assistance.

Clear Coating

For 10 year outdoor durability of the ink, clear coating using Overprint Clear UVTS25 is required.

Additionally, OL-1000, when laminated over standard UVTS-NazDar Ink traffic colors, will extend the outdoor durability to 10 years.

UVTS-NazDar Printing Inks continued...

Ink Clean-up

Screens and other printing equipment should be cleaned immediately with Avery Dennison UVTS-NazDar Screen Wash or as soon as possible after use. Though UV inks will not cure in the screen like solvent inks, they are susceptible to premature cure if exposed to ambient UV light, such as direct sunlight. Exposure to less UV intensive light sources, such as interior lighting, should not be a problem provided the screen is not left unattended for a prolonged period. The ink can be left in the screen for short periods of time, such as a lunch break, without causing cleaning problems, provided the screen is not exposed to direct sunlight.

Screens used to print Avery Dennison UVTS-NazDar Inks are cleaned like screens used for standard solvent inks. The ink should be removed from the print screen using UVTS-NazDar Screen Wash and clean-up rags. Do not re-use ink that is removed from the screen.

Caution: Wearing gloves, safety glasses, and other safety equipment is required when working with inks and cleaning solvents.

Warranty:

WARRANTY: All statements, technical information and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its purposes. Avery Dennison products are warranted to be free from defects in material and workmanship for either one year (or the period stated on the specific product information literature in effect at time of delivery, if longer) from date of shipment if said product is properly stored and applied. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited to repair or replacement of defective product without charge at Avery Dennison's plant or at the location of product (at Avery Dennison's election), or in the event replacement or repairs is not commercially practical, to Avery Dennison's issuing Purchaser a credit reasonable in light of the defect in the product.

Avery Dennison's liability for defective products shall not exceed the purchase price paid therefore by Purchaser and in no event shall Avery Dennison be responsible for any incidental or consequential damages whether foreseeable or not, caused by defects in such product, whether such damage occurs or is discovered before or after replacement or credit, and whether or not such damage is caused by Avery Dennison's negligence.

NO EXPRESS WARRANTIES AND NO IMPLIED WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE (EXCEPT AS TO TITLE), OTHER THAN THOSE EXPRESSLY SET FORTH ABOVE WHICH ARE MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.

Avery Dennison , 6565 W. Howard, Niles, IL 60714, USA, 1-800-327-5917, www.reflectives.averydennison.com

Avery Dennison Ink Recommendation Guide

Revised 07NOV05

Compatibility & Durability:

Avery Dennison recommends the use of the following series of inks to assure user satisfaction and conformance with warranty requirements. Because the choice of ink series can determine the durability, transparency and sign reflectivity level, it is important that the correct series of ink be matched with the reflective sheeting used. Differing environmental conditions found in specific regions of the country may result in the ability of Avery Dennison to increase the period of ink durability and warranty for select ink colors and series. Any exceptions to the information contained below must be confirmed in writing by Avery Dennison to become binding. Please contact Avery Dennison for further information.

Application & Conversion:

Complete information to the user for proper application, storage, and other requirements is available from your Avery Dennison representative, from the Avery Dennison web-site www.reflectives.averydennison.com, or on request. Please reference the Instructional Bulletin number for each series of ink shown in the charts.

1. RECOMMENDATION BY SHEETING SERIES

SHEETING	INK SERIES
T-1200 / T-1500 / T-1600	7TS 10TS
T-2200 / T-2500 / T-2600	7TS 10TS
T-5500A	4930
T-6500	4930 UVTS NazDar
T-7500 MVP	4930 UVTS NazDar
T-7511 / T-7513 MVP	4930 UVTS NazDar
W-7514	4930 UVTS NazDar
T-9500 Omni View	4930 UVTS NazDar

Ink Recommendation Guide...

2. RECOMMENDATION BY INK SERIES

INK	SHEETING SERIES
<p style="text-align: center;">7TS</p> <ul style="list-style-type: none"> • 7-year durability • 10-year durability with clear coat or OL-1000 Overlay Film • 157 mesh screen • Refer to Instructional Bulletin #8.37 	<p style="text-align: center;">T-1200 / T-1500 / T-1600 T-2200 / T-2500 / T-2600</p>
<p style="text-align: center;">10TS</p> <ul style="list-style-type: none"> • 10-year durability • 2-component ink system • 157 mesh screen • Refer to Instructional Bulletin #8.32 	<p style="text-align: center;">T-1200 / T-1500 / T-1600 T-2200 / T-2500 / T-2600</p>
<p style="text-align: center;">4930</p> <ul style="list-style-type: none"> • Durability to match that of the base sheeting series • 157 – 180 mesh screen • Refer to Instructional Bulletin #8.40 	<p style="text-align: center;">T-5500A T-6500 T-7500 / T-7511 / T-7513 MVP W-7514 T-9500 Omni View</p>
<p style="text-align: center;">UVTS NazDar</p> <ul style="list-style-type: none"> • 10-year durability with UV Clear or OL-1000 Overlay Film • 305 mesh screen • Refer to Instructional Bulletin #8.38 	<p style="text-align: center;">T-6500 T-7500 / T-7511 / T-7513 MVP W-7514 T-9500 Omni View</p>

Warranty:

WARRANTY: All statements, technical information and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its purposes. Avery Dennison products are warranted to be free from defects in material and workmanship for either one year (or the period stated on the specific product information literature in effect at time of delivery, if longer) from date of shipment if said product is properly stored and applied. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited to repair or replacement of defective product without charge at Avery Dennison's plant or at the location of product (at Avery Dennison's election), or in the event replacement or repairs is not commercially practical, to Avery Dennison's issuing Purchaser a credit reasonable in light of the defect in the product.

Avery Dennison's liability for defective products shall not exceed the purchase price paid therefore by Purchaser and in no event shall Avery Dennison be responsible for any incidental or consequential damages whether foreseeable or not, caused by defects in such product, whether such damage occurs or is discovered before or after replacement or credit, and whether or not such damage is caused by Avery Dennison's negligence.

NO EXPRESS WARRANTIES AND NO IMPLIED WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE (EXCEPT AS TO TITLE), OTHER THAN THOSE EXPRESSLY SET FORTH ABOVE WHICH ARE MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.

Avery Dennison , 6565 W. Howard, Niles, IL 60714, USA, 1-800-327-5917, www.reflectives.averydennison.com

