

PLASTICAL XG

**Nazdar PANTONE®
Matching System**

**Version 3.0
SMS Base Colors**

Plastijet XG

Seritone Matching System

PANTONE® Shades Simulated From Seritone Base Colors

This booklet furnishes the necessary formulas to simulate all the "C" colors of the PANTONE Color Formula Guide, except Double print, Fluorescent, and Metallic Colors.

Each formula was printed through a 280 (110/cm) monofilament screen with a 75 durometer sharp edge squeegee, on white pressure sensitive vinyl, and the ink was thinned 15% with XG-TH. All formulas are presented by weight. However, due to variations in ink film thickness, screen mesh, and other variables, some formulas may need adjustments.

The Seritone Matching System (SMS) has been designed to enable screen printers to simulate almost any shade from nine SMS Base Colors plus Shading Black, Tinting White, and Mixing Clear.

Each SMS Base Color has been carefully selected for its cleanliness of tone, resistance to fading, and suitability for intermixing. In addition, each ink has been formulated to be free of lead and other heavy metals.

Although every care is taken in producing these formulations, variations in substrates and printing conditions will affect color achieved. Nazdar assumes no responsibility for actual color achieved. For this reason, all formulations must be proofed, prior to production run, to ensure color accuracy.

In some cases, to accurately simulate a PANTONE shade, considerable amounts of Mixing Clear and/or Tinting White are in the formulation. The exterior durability of color mixes with high percentages of Mixing Clear and/or Tinting White will be reduced. The Technical Services Department, in many cases, can provide an alternate PANTONE simulation formula yielding improved exterior durability.

The SMS Base Colors are listed below and are available in single gallon containers:

DESCRIPTION	
XG-064 SMS Yellow GS (Green Shade)	XG-165 SMS Magenta
XG-066 SMS Yellow RS (Red Shade)	XG-230 SMS Blue
XG-114 SMS Orange	XG-325 SMS Green
XG-121 SMS Red YS (Yellow Shade)	XG-TW SMS Tinting White
XG-127 SMS Violet	XG-SB Shading Black
XG-164 SMS Red BS (Blue Shade)	XG-MX Mixing Clear

Nazdar's color mixing ink formulations for screen process printing produce only simulations of PANTONE Colors in this color reproduction method due to differences in ink film, opacity and pigment selection. The pigment selection used in blending screen process inks may cause metamerism. Pantone, Inc. assumes no responsibility for formula accuracy. PANTONE® is Pantone, Inc.'s checkstandard trademark for color. Portions© Pantone, Inc., 1963,1991.C=Coated Paper

Plastijet XG

PANTONE Yellow 012 C XG-064 48.08 XG-TW 38.46 XG-066 13.46	Formula	PANTONE Process Yellow C XG-TW 50.00 XG-064 50.00	Formula	PANTONE Process Magenta C XG-165 67.40 XG-TW 25.20 XG-121 7.40	Formula	PANTONE Process Cyan C XG-TW 86.00 XG-230 12.40 XG-325 1.60	Formula
PANTONE Process Black C XG-TW 48.70 XG-301 18.90 XG-066 16.70 XG-165 15.70	Formula	PANTONE 100 C XG-TW 92.57 XG-064 7.43	Formula	PANTONE 101 C XG-TW 76.92 XG-064 23.08	Formula	PANTONE 102 C XG-TW 50.00 XG-064 50.00	Formula
PANTONE Yellow C XG-064 100.00	Formula	PANTONE 103 C XG-064 95.04 XG-066 3.40 XG-301 1.56	Formula	PANTONE 104 C XG-064 92.31 XG-066 5.13 XG-301 2.56	Formula	PANTONE 105 C XG-064 63.20 XG-MX 31.46 XG-301 5.34	Formula
PANTONE 106 C XG-TW 84.13 XG-064 11.74 XG-066 4.13	Formula	PANTONE 107 C XG-TW 50.81 XG-064 39.89 XG-066 9.30	Formula	PANTONE 108 C XG-TW 49.04 XG-064 38.50 XG-066 12.46	Formula	PANTONE 109 C XG-064 47.66 XG-TW 37.47 XG-066 14.87	Formula

Plastijet XG

PANTONE 110 C XG-066 38.22 XG-TW 34.48 XG-064 26.10 XG-301 1.20	Formula	PANTONE 111 C XG-064 95.79 XG-301 2.66 XG-165 1.55	Formula	PANTONE 112 C XG-064 91.58 XG-301 3.75 XG-TW 2.82 XG-165 1.85	Formula	PANTONE 113 C XG-TW 91.67 XG-066 8.33	Formula
PANTONE 114 C XG-TW 89.99 XG-066 10.01	Formula	PANTONE 115 C XG-TW 87.18 XG-066 12.82	Formula	PANTONE 116 C XG-064 46.68 XG-TW 45.27 XG-066 6.81 XG-114 1.24	Formula	PANTONE 117 C XG-064 37.36 XG-TW 36.62 XG-066 23.14 XG-301 1.71 XG-114 1.17	Formula
PANTONE 118 C XG-066 63.67 XG-TW 31.32 XG-165 3.54 XG-230 1.47	Formula	PANTONE 119 C XG-TW 57.63 XG-066 31.44 XG-165 8.21 XG-230 2.72	Formula	PANTONE 120 C XG-TW 96.29 XG-066 3.51 XG-114 0.20	Formula	PANTONE 121 C XG-TW 94.55 XG-064 4.92 XG-066 0.53	Formula
PANTONE 122 C XG-TW 89.19 XG-066 9.09 XG-064 1.20 XG-114 0.52	Formula	PANTONE 123 C XG-TW 52.96 XG-064 42.37 XG-114 2.37 XG-066 2.30	Formula	PANTONE 124 C XG-064 88.86 XG-TW 7.60 XG-121 3.02 XG-301 0.52	Formula	PANTONE 125 C XG-064 89.98 XG-TW 4.47 XG-121 3.29 XG-301 2.26	Formula

Plastijet XG

PANTONE 126 C XG-064 82.96 XG-TW 10.28 XG-301 3.61 XG-121 3.15	Formula	PANTONE 1205 C XG-TW 97.69 XG-064 1.92 XG-121 0.39	Formula	PANTONE 1215 C XG-TW 92.25 XG-064 7.38 XG-121 0.37	Formula	PANTONE 1225 C XG-TW 75.08 XG-064 24.02 XG-121 0.90	Formula
PANTONE 1235 C XG-064 69.80 XG-TW 26.90 XG-114 3.30	Formula	PANTONE 1245 C XG-064 70.00 XG-TW 24.00 XG-114 4.00 XG-301 2.00	Formula	PANTONE 1255 C XG-064 69.31 XG-TW 23.76 XG-114 3.96 XG-301 2.97	Formula	PANTONE 1265 C XG-064 95.80 XG-121 2.80 XG-301 1.40	Formula
PANTONE 127 C XG-TW 88.42 XG-064 11.29 XG-114 0.17 XG-164 0.12	Formula	PANTONE 128 C XG-TW 78.27 XG-064 21.32 XG-164 0.31 XG-114 0.10	Formula	PANTONE 129 C XG-TW 66.32 XG-064 33.09 XG-164 0.49 XG-114 0.10	Formula	PANTONE 130 C XG-064 86.32 XG-TW 12.00 XG-164 1.68	Formula
PANTONE 131 C XG-064 96.88 XG-164 2.07 XG-301 1.05	Formula	PANTONE 132 C XG-064 92.51 XG-165 4.72 XG-301 2.77	Formula	PANTONE 133 C XG-064 59.50 XG-MX 20.40 XG-TW 10.20 XG-301 7.80 XG-164 2.10	Formula	PANTONE 134 C XG-TW 87.75 XG-064 11.76 XG-121 0.49	Formula

Plastijet XG

PANTONE 135 C XG-TW 71.00 XG-064 27.30 XG-121 1.70	Formula	PANTONE 136 C XG-TW 70.89 XG-064 27.26 XG-121 1.85	Formula	PANTONE 137 C XG-064 93.80 XG-114 6.20	Formula	PANTONE 138 C XG-064 93.86 XG-121 5.93 XG-301 0.21	Formula
PANTONE 139 C XG-064 91.13 XG-121 6.26 XG-301 2.61	Formula	PANTONE 140 C XG-064 85.99 XG-121 8.52 XG-301 5.49	Formula	PANTONE 1345 C XG-TW 95.11 XG-064 3.81 XG-114 1.08	Formula	PANTONE 1355 C XG-TW 92.07 XG-064 6.37 XG-114 1.56	Formula
PANTONE 1365 C XG-TW 83.47 XG-064 13.37 XG-114 3.16	Formula	PANTONE 1375 C XG-TW 55.83 XG-064 34.70 XG-114 9.47	Formula	PANTONE 1385 C XG-064 70.41 XG-TW 14.40 XG-114 13.59 XG-301 1.60	Formula	PANTONE 1395 C XG-TW 33.69 XG-066 33.12 XG-MX 19.18 XG-165 10.24 XG-301 3.77	Formula
PANTONE 1405 C XG-066 43.48 XG-TW 20.09 XG-MX 18.46 XG-301 9.51 XG-165 8.46	Formula	PANTONE 141 C XG-TW 83.96 XG-064 15.67 XG-164 0.37	Formula	PANTONE 142 C XG-TW 67.49 XG-064 29.90 XG-121 2.39 XG-325 0.22	Formula	PANTONE 143 C XG-TW 66.92 XG-064 29.65 XG-121 3.16 XG-325 0.27	Formula

Plastijet XG

PANTONE 144 C XG-066 62.60 XG-TW 30.90 XG-165 6.20 XG-301 0.30	Formula	PANTONE 145 C XG-064 96.39 XG-164 2.57 XG-301 1.04	Formula	PANTONE 146 C XG-064 95.19 XG-164 3.09 XG-301 1.72	Formula	PANTONE 147 C XG-064 92.33 XG-301 4.67 XG-164 3.00	Formula
PANTONE 148 C XG-TW 92.26 XG-064 6.55 XG-121 1.19	Formula	PANTONE 149 C XG-TW 88.28 XG-064 10.36 XG-121 1.36	Formula	PANTONE 150 C XG-TW 69.87 XG-064 24.61 XG-114 5.52	Formula	PANTONE 151 C XG-064 77.80 XG-114 22.20	Formula
PANTONE 152 C XG-064 88.03 XG-114 8.93 XG-121 2.44 XG-301 0.60	Formula	PANTONE 153 C XG-064 91.67 XG-121 7.67 XG-301 0.66	Formula	PANTONE 154 C XG-064 88.25 XG-121 9.31 XG-301 2.44	Formula	PANTONE 1485 C XG-TW 92.64 XG-066 4.92 XG-114 2.06 XG-164 0.38	Formula
PANTONE 1495 C XG-TW 78.37 XG-066 14.71 XG-114 6.32 XG-121 0.60	Formula	PANTONE 1505 C XG-TW 65.72 XG-114 18.07 XG-066 16.21	Formula	PANTONE Orange 021 C XG-066 59.10 XG-114 40.90	Formula	PANTONE 1525 C XG-114 52.16 XG-064 46.49 XG-301 1.35	Formula

Plastijet XG

PANTONE 1535 C XG-114 51.47 XG-064 45.86 XG-301 2.67	Formula	PANTONE 1545 C XG-114 60.87 XG-301 21.74 XG-121 17.39	Formula	PANTONE 155 C XG-TW 95.34 XG-064 4.53 XG-164 0.13	Formula	PANTONE 156 C XG-TW 93.69 XG-064 6.06 XG-164 0.25	Formula
PANTONE 157 C XG-TW 76.62 XG-064 21.76 XG-164 1.62	Formula	PANTONE 158 C XG-TW 49.30 XG-066 36.40 XG-165 14.20 XG-301 0.10	Formula	PANTONE 159 C XG-064 94.85 XG-164 4.72 XG-301 0.43	Formula	PANTONE 160 C XG-064 91.70 XG-164 6.04 XG-301 2.26	Formula
PANTONE 161 C XG-064 84.19 XG-164 9.58 XG-301 6.23	Formula	PANTONE 1555 C XG-TW 86.52 XG-064 10.00 XG-121 3.48	Formula	PANTONE 1565 C XG-TW 77.69 XG-064 17.41 XG-121 4.90	Formula	PANTONE 1575 C XG-TW 67.48 XG-066 18.40 XG-114 8.59 XG-121 5.53	Formula
PANTONE 1585 C XG-TW 45.90 XG-066 34.20 XG-114 14.40 XG-121 5.50	Formula	PANTONE 1595 C XG-064 83.40 XG-121 15.61 XG-301 0.99	Formula	PANTONE 1605 C XG-064 80.83 XG-121 15.46 XG-301 3.71	Formula	PANTONE 1615 C XG-064 77.29 XG-121 18.32 XG-301 4.39	Formula

Plastijet XG

PANTONE 162 C XG-TW 93.46 XG-064 3.74 XG-121 2.80	Formula	PANTONE 163 C XG-TW 83.63 XG-064 12.28 XG-121 4.09	Formula	PANTONE 164 C XG-121 58.14 XG-066 23.26 XG-TW 9.30 XG-114 9.30	Formula	PANTONE 165 C XG-114 53.30 XG-TW 41.40 XG-066 5.30	Formula
PANTONE 166 C XG-064 80.55 XG-121 19.07 XG-301 0.38	Formula	PANTONE 167 C XG-064 81.53 XG-121 16.79 XG-301 1.68	Formula	PANTONE 168 C XG-064 67.34 XG-121 25.45 XG-301 7.21	Formula	PANTONE 1625 C XG-TW 95.40 XG-114 2.60 XG-121 2.00	Formula
PANTONE 1635 C XG-TW 89.90 XG-114 7.00 XG-121 3.10	Formula	PANTONE 1645 C XG-TW 80.60 XG-114 16.20 XG-121 3.20	Formula	PANTONE 1655 C XG-TW 59.90 XG-114 35.70 XG-121 4.40	Formula	PANTONE 1665 C XG-MX 59.70 XG-114 29.90 XG-121 9.00 XG-301 1.40	Formula
PANTONE 1675 C XG-MX 51.70 XG-114 31.60 XG-121 11.70 XG-301 5.00	Formula	PANTONE 1685 C XG-114 52.30 XG-MX 28.50 XG-121 10.90 XG-301 8.30	Formula	PANTONE 169 C XG-TW 96.30 XG-121 2.10 XG-114 1.60	Formula	PANTONE 170 C XG-TW 81.30 XG-121 9.10 XG-114 6.80 XG-MX 2.80	Formula

Plastijet XG

PANTONE 171 C XG-TW 42.50 XG-114 31.90 XG-MX 13.30 XG-121 12.30	Formula	PANTONE 172 C XG-114 55.00 XG-TW 36.30 XG-121 8.70	Formula	PANTONE 173 C XG-114 46.90 XG-MX 39.10 XG-121 8.30 XG-164 3.00 XG-301 2.70	Formula	PANTONE 174 C XG-114 35.40 XG-MX 26.30 XG-121 22.80 XG-164 8.10 XG-301 7.40	Formula
PANTONE 175 C XG-121 49.60 XG-164 17.70 XG-MX 16.60 XG-301 16.10	Formula	PANTONE 176 C XG-TW 96.07 XG-121 3.26 XG-114 0.67	Formula	PANTONE 177 C XG-TW 87.19 XG-121 10.28 XG-114 2.53	Formula	PANTONE 178 C XG-TW 78.58 XG-121 15.64 XG-114 5.78	Formula
PANTONE Warm Red C XG-TW 39.37 XG-114 37.20 XG-121 21.85 XG-164 1.58	Formula	PANTONE 179 C XG-TW 44.45 XG-121 43.00 XG-114 12.55	Formula	PANTONE 180 C XG-TW 57.65 XG-121 24.76 XG-114 15.95 XG-301 1.64	Formula	PANTONE 181 C XG-TW 32.33 XG-121 29.77 XG-MX 19.16 XG-114 12.76 XG-301 5.98	Formula
PANTONE 1765 C XG-TW 93.42 XG-121 6.00 XG-114 0.58	Formula	PANTONE 1775 C XG-TW 89.77 XG-121 9.19 XG-114 1.04	Formula	PANTONE 1785 C XG-TW 64.97 XG-121 31.36 XG-114 3.67	Formula	PANTONE 1788 C XG-MX 70.30 XG-121 29.70	Formula

Plastijet XG

PANTONE 1795 C XG-121 59.60 XG-TW 36.45 XG-114 3.95	Formula	PANTONE 1805 C XG-121 54.45 XG-TW 37.59 XG-114 5.93 XG-301 2.03	Formula	PANTONE 1815 C XG-121 71.22 XG-TW 23.00 XG-301 5.78	Formula	PANTONE 1767 C XG-TW 96.50 XG-121 3.50	Formula
PANTONE 1777 C XG-TW 75.77 XG-121 24.23	Formula	PANTONE 1787 C XG-121 52.00 XG-TW 48.00	Formula	PANTONE Red 032 C XG-121 54.63 XG-TW 39.59 XG-114 5.78	Formula	PANTONE 1797 C XG-121 74.79 XG-TW 24.32 XG-301 0.89	Formula
PANTONE 1807 C XG-121 71.79 XG-TW 24.79 XG-301 3.42	Formula	PANTONE 1817 C XG-TW 33.33 XG-114 32.04 XG-164 21.68 XG-301 12.95	Formula	PANTONE 182 C XG-TW 97.88 XG-121 2.12	Formula	PANTONE 183 C XG-TW 90.13 XG-121 9.87	Formula
PANTONE 184 C XG-TW 73.23 XG-121 26.77	Formula	PANTONE 185 C XG-121 43.90 XG-MX 39.91 XG-TW 9.58 XG-164 6.61	Formula	PANTONE 186 C XG-121 46.68 XG-MX 26.75 XG-164 19.20 XG-TW 7.37	Formula	PANTONE 187 C XG-121 54.61 XG-165 35.10 XG-TW 9.48 XG-325 0.81	Formula

Plastijet XG

PANTONE 188 C XG-121 43.42 XG-165 30.59 XG-MX 15.42 XG-TW 6.89 XG-325 3.68	Formula	PANTONE 189 C XG-TW 94.47 XG-121 5.53	Formula	PANTONE 190 C XG-TW 84.83 XG-121 11.63 XG-165 2.16 XG-164 1.38	Formula	PANTONE 191 C XG-TW 61.21 XG-121 27.95 XG-165 7.93 XG-164 2.91	Formula
PANTONE 192 C XG-121 53.00 XG-TW 25.60 XG-165 15.40 XG-164 6.00	Formula	PANTONE 193 C XG-121 46.11 XG-164 21.69 XG-TW 17.82 XG-165 13.39 XG-301 0.99	Formula	PANTONE 194 C XG-121 45.73 XG-165 33.96 XG-TW 16.55 XG-301 3.76	Formula	PANTONE 195 C XG-121 40.79 XG-TW 26.11 XG-165 25.08 XG-301 8.02	Formula
PANTONE 1895 C XG-TW 97.68 XG-121 2.22 XG-165 0.10	Formula	PANTONE 1905 C XG-TW 93.88 XG-121 5.34 XG-164 0.67 XG-165 0.11	Formula	PANTONE 1915 C XG-TW 75.81 XG-121 18.10 XG-164 5.48 XG-165 0.61	Formula	PANTONE 1925 C XG-121 40.04 XG-TW 37.98 XG-165 11.39 XG-164 10.59	Formula
PANTONE 1935 C XG-121 35.70 XG-TW 27.00 XG-164 25.50 XG-165 11.60 XG-301 0.20	Formula	PANTONE 1945 C XG-TW 37.56 XG-121 32.61 XG-164 28.28 XG-301 1.55	Formula	PANTONE 1955 C XG-TW 42.82 XG-121 36.14 XG-164 17.74 XG-301 3.30	Formula	PANTONE 196 C XG-TW 98.29 XG-164 0.88 XG-064 0.83	Formula

Plastijet XG

PANTONE 197 C XG-TW 94.08 XG-121 5.51 XG-164 0.41	Formula	PANTONE 198 C XG-TW 73.52 XG-121 23.54 XG-164 2.94	Formula	PANTONE 199 C XG-121 49.84 XG-TW 37.83 XG-164 12.33	Formula	PANTONE 200 C XG-121 48.96 XG-TW 32.24 XG-164 17.81 XG-301 0.99	Formula
PANTONE 201 C XG-165 45.88 XG-121 44.56 XG-TW 7.42 XG-325 2.14	Formula	PANTONE 202 C XG-165 53.40 XG-121 42.07 XG-325 3.12 XG-TW 1.41	Formula	PANTONE 203 C XG-TW 96.24 XG-121 1.94 XG-165 1.82	Formula	PANTONE 204 C XG-TW 87.86 XG-165 6.86 XG-121 5.28	Formula
PANTONE 205 C XG-TW 69.68 XG-165 19.46 XG-121 10.86	Formula	PANTONE 206 C XG-165 69.50 XG-121 22.24 XG-TW 8.26	Formula	PANTONE 207 C XG-165 56.25 XG-121 22.68 XG-TW 19.65 XG-301 1.42	Formula	PANTONE 208 C XG-165 53.30 XG-121 24.16 XG-TW 18.65 XG-301 3.89	Formula
PANTONE 209 C XG-165 46.57 XG-TW 24.46 XG-121 23.45 XG-301 5.52	Formula	PANTONE 210 C XG-MX 91.93 XG-165 5.63 XG-164 1.88 XG-064 0.56	Formula	PANTONE 211 C XG-MX 94.74 XG-164 5.26	Formula	PANTONE 212 C XG-MX 89.74 XG-164 10.26	Formula

Plastijet XG

PANTONE 213 C XG-MX 83.50 XG-164 16.50	Formula	PANTONE 214 C XG-MX 66.23 XG-164 26.49 XG-165 6.62 XG-301 0.66	Formula	PANTONE 215 C XG-MX 64.94 XG-164 25.97 XG-165 6.49 XG-301 2.60	Formula	PANTONE 216 C XG-MX 63.05 XG-164 25.21 XG-165 6.30 XG-301 5.44	Formula
PANTONE 217 C XG-TW 98.90 XG-164 1.10	Formula	PANTONE 218 C XG-TW 88.94 XG-165 5.95 XG-164 5.11	Formula	PANTONE 219 C XG-TW 63.80 XG-165 26.50 XG-164 9.70	Formula	PANTONE Rubine Red C XG-165 48.30 XG-164 27.70 XG-TW 17.80 XG-121 6.20	Formula
PANTONE 220 C XG-165 65.41 XG-164 19.03 XG-TW 14.37 XG-301 1.19	Formula	PANTONE 221 C XG-165 57.87 XG-TW 20.52 XG-164 19.21 XG-301 2.40	Formula	PANTONE 222 C XG-165 45.80 XG-164 26.30 XG-TW 18.60 XG-121 9.30	Formula	PANTONE 223 C XG-TW 90.40 XG-165 9.60	Formula
PANTONE 224 C XG-TW 79.01 XG-165 20.99	Formula	PANTONE 225 C XG-165 37.03 XG-TW 34.15 XG-MX 28.82	Formula	PANTONE 226 C XG-165 68.20 XG-TW 30.49 XG-164 1.31	Formula	PANTONE 227 C XG-165 84.58 XG-TW 8.95 XG-164 6.32 XG-301 0.15	Formula

Plastijet XG

PANTONE 228 C XG-165 74.99 XG-TW 12.88 XG-164 6.71 XG-301 5.42	Formula	PANTONE 229 C XG-164 45.59 XG-TW 44.94 XG-301 9.47	Formula	PANTONE 230 C XG-MX 96.16 XG-165 2.88 XG-164 0.96	Formula	PANTONE 231 C XG-MX 88.71 XG-165 8.06 XG-164 3.23	Formula
PANTONE 232 C XG-MX 72.92 XG-165 20.83 XG-164 6.25	Formula	PANTONE Rhodamine Red C XG-MX 65.30 XG-165 30.70 XG-164 4.00	Formula	PANTONE 233 C XG-165 61.73 XG-MX 37.04 XG-127 1.23	Formula	PANTONE 234 C XG-165 59.80 XG-MX 36.27 XG-301 2.95 XG-127 0.98	Formula
PANTONE 235 C XG-165 58.87 XG-MX 30.30 XG-164 5.19 XG-301 4.76 XG-127 0.88	Formula	PANTONE 236 C XG-TW 94.70 XG-165 5.30	Formula	PANTONE 237 C XG-TW 85.36 XG-165 14.64	Formula	PANTONE 238 C XG-TW 69.02 XG-165 30.98	Formula
PANTONE 239 C XG-TW 56.87 XG-165 43.13	Formula	PANTONE 240 C XG-165 56.42 XG-TW 43.41 XG-301 0.17	Formula	PANTONE 241 C XG-165 63.10 XG-TW 35.11 XG-301 1.79	Formula	PANTONE 242 C XG-TW 64.36 XG-164 30.35 XG-301 5.29	Formula

Plastijet XG

PANTONE 2365 C XG-MX 93.67 XG-165 6.23 XG-230 0.10	Formula	PANTONE 2375 C XG-MX 73.14 XG-165 26.60 XG-230 0.26	Formula	PANTONE 2385 C XG-MX 49.79 XG-165 49.79 XG-230 0.42	Formula	PANTONE 2395 C XG-165 71.70 XG-MX 27.70 XG-230 0.60	Formula
PANTONE 2405 C XG-165 75.05 XG-MX 23.45 XG-301 0.94 XG-230 0.56	Formula	PANTONE 2415 C XG-165 76.92 XG-MX 20.51 XG-301 2.06 XG-230 0.51	Formula	PANTONE 2425 C XG-165 56.70 XG-MX 36.08 XG-301 6.19 XG-230 1.03	Formula	PANTONE 243 C XG-MX 95.00 XG-165 4.90 XG-230 0.10	Formula
PANTONE 244 C XG-MX 90.54 XG-165 9.36 XG-230 0.10	Formula	PANTONE 245 C XG-MX 81.22 XG-165 18.60 XG-230 0.18	Formula	PANTONE 246 C XG-165 58.00 XG-MX 41.50 XG-230 0.50	Formula	PANTONE 247 C XG-165 73.42 XG-MX 25.32 XG-230 0.63 XG-301 0.63	Formula
PANTONE 248 C XG-165 72.05 XG-MX 24.85 XG-301 2.48 XG-230 0.62	Formula	PANTONE 249 C XG-165 89.78 XG-301 8.67 XG-230 1.55	Formula	PANTONE 250 C XG-TW 48.74 XG-MX 48.72 XG-165 2.44 XG-230 0.10	Formula	PANTONE 251 C XG-MX 90.63 XG-165 9.07 XG-230 0.30	Formula

Plastijet XG

PANTONE 252 C XG-MX 69.31 XG-165 29.70 XG-230 0.99	Formula	PANTONE Purple C XG-MX 45.46 XG-165 45.45 XG-127 9.09	Formula	PANTONE 253 C XG-165 61.35 XG-MX 36.81 XG-230 1.84	Formula	PANTONE 254 C XG-165 75.18 XG-MX 22.56 XG-230 2.26	Formula
PANTONE 255 C XG-165 75.38 XG-MX 16.75 XG-301 5.02 XG-230 2.85	Formula	PANTONE 256 C XG-TW 96.83 XG-165 2.08 XG-127 0.73 XG-301 0.36	Formula	PANTONE 257 C XG-TW 93.85 XG-165 4.04 XG-127 1.41 XG-301 0.70	Formula	PANTONE 258 C XG-TW 62.99 XG-165 27.56 XG-127 9.45	Formula
PANTONE 259 C XG-165 61.70 XG-127 21.00 XG-TW 17.30	Formula	PANTONE 260 C XG-165 60.19 XG-127 20.39 XG-TW 17.48 XG-301 1.94	Formula	PANTONE 261 C XG-165 60.55 XG-127 19.27 XG-TW 16.51 XG-301 3.67	Formula	PANTONE 262 C XG-165 60.00 XG-TW 16.92 XG-127 16.15 XG-301 6.93	Formula
PANTONE 2562 C XG-TW 93.96 XG-165 3.02 XG-127 3.02	Formula	PANTONE 2572 C XG-TW 77.29 XG-165 9.18 XG-MX 7.25 XG-127 6.28	Formula	PANTONE 2582 C XG-TW 56.60 XG-165 17.93 XG-MX 14.15 XG-127 11.32	Formula	PANTONE 2592 C XG-MX 58.70 XG-165 22.50 XG-127 18.80	Formula

Plastijet XG

PANTONE 2602 C XG-MX 54.63 XG-127 23.15 XG-165 20.83 XG-301 1.39	Formula	PANTONE 2612 C XG-MX 53.88 XG-127 22.83 XG-165 20.55 XG-301 2.74	Formula	PANTONE 2622 C XG-MX 39.46 XG-165 21.07 XG-TW 16.73 XG-127 16.72 XG-301 6.02	Formula	PANTONE 2563 C XG-TW 92.04 XG-165 4.05 XG-127 3.91	Formula
PANTONE 2573 C XG-TW 77.22 XG-165 13.51 XG-127 9.27	Formula	PANTONE 2583 C XG-TW 58.39 XG-165 25.55 XG-127 16.06	Formula	PANTONE 2593 C XG-165 35.10 XG-MX 22.70 XG-TW 21.40 XG-127 20.80	Formula	PANTONE 2603 C XG-165 33.11 XG-TW 23.02 XG-127 21.51 XG-MX 21.42 XG-301 0.94	Formula
PANTONE 2613 C XG-165 34.90 XG-TW 21.79 XG-127 20.36 XG-MX 20.27 XG-301 2.68	Formula	PANTONE 2623 C XG-165 39.60 XG-TW 19.68 XG-127 18.39 XG-MX 18.30 XG-301 4.03	Formula	PANTONE 2567 C XG-TW 75.95 XG-MX 14.06 XG-127 7.03 XG-165 2.96	Formula	PANTONE 2577 C XG-TW 58.39 XG-MX 24.33 XG-127 12.17 XG-165 5.11	Formula
PANTONE 2587 C XG-TW 36.90 XG-MX 36.90 XG-127 18.45 XG-165 7.75	Formula	PANTONE 2597 C XG-MX 48.80 XG-127 34.10 XG-165 17.10	Formula	PANTONE 2607 C XG-MX 46.73 XG-127 35.51 XG-165 15.89 XG-301 1.87	Formula	PANTONE 2617 C XG-MX 45.04 XG-127 36.04 XG-165 15.32 XG-301 3.60	Formula

Plastijet XG

PANTONE 2627 C XG-MX 43.48 XG-127 36.52 XG-165 14.78 XG-301 5.22	Formula	PANTONE 263 C XG-TW 98.00 XG-127 1.70 XG-165 0.20 XG-230 0.10	Formula	PANTONE 264 C XG-TW 68.15 XG-MX 25.10 XG-127 5.74 XG-165 0.72 XG-230 0.29	Formula	PANTONE 265 C XG-MX 50.43 XG-TW 36.02 XG-127 11.53 XG-165 1.44 XG-230 0.58	Formula
PANTONE 266 C XG-MX 68.20 XG-127 30.50 XG-230 1.30	Formula	PANTONE 267 C XG-MX 50.72 XG-127 44.93 XG-230 2.90 XG-301 1.45	Formula	PANTONE 268 C XG-127 50.54 XG-MX 37.63 XG-165 6.45 XG-301 3.23 XG-230 2.15	Formula	PANTONE 269 C XG-127 47.00 XG-MX 35.00 XG-165 8.00 XG-301 8.00 XG-230 2.00	Formula
PANTONE 2635 C XG-TW 96.92 XG-127 3.08	Formula	PANTONE 2645 C XG-TW 94.41 XG-127 5.59	Formula	PANTONE 2655 C XG-TW 86.84 XG-127 12.76 XG-165 0.40	Formula	PANTONE 2665 C XG-TW 71.12 XG-127 25.78 XG-165 3.10	Formula
PANTONE Violet C XG-MX 63.72 XG-127 35.74 XG-230 0.54	Formula	PANTONE 2685 C XG-127 66.28 XG-TW 33.72	Formula	PANTONE 2695 C XG-127 41.50 XG-TW 27.20 XG-165 25.20 XG-301 4.80 XG-066 1.30	Formula	PANTONE 270 C XG-TW 96.15 XG-127 3.31 XG-230 0.36 XG-301 0.18	Formula

Plastijet XG

PANTONE 271 C XG-TW 91.46 XG-127 7.48 XG-230 0.76 XG-301 0.30	Formula	PANTONE 272 C XG-TW 78.13 XG-127 19.14 XG-230 1.95 XG-301 0.78	Formula	PANTONE 273 C XG-127 66.40 XG-MX 15.10 XG-230 10.60 XG-TW 7.90	Formula	PANTONE 274 C XG-127 57.69 XG-MX 32.05 XG-230 6.41 XG-301 3.85	Formula
PANTONE 275 C XG-127 55.90 XG-MX 31.06 XG-301 6.83 XG-230 6.21	Formula	PANTONE 276 C XG-127 53.25 XG-MX 29.59 XG-301 11.24 XG-230 5.92	Formula	PANTONE 2705 C XG-TW 94.95 XG-127 4.28 XG-230 0.77	Formula	PANTONE 2715 C XG-TW 89.46 XG-127 9.51 XG-230 1.03	Formula
PANTONE 2725 C XG-TW 73.82 XG-127 23.57 XG-230 2.61	Formula	PANTONE 2735 C XG-127 47.34 XG-MX 32.81 XG-TW 15.94 XG-230 3.91	Formula	PANTONE 2745 C XG-127 69.89 XG-230 27.06 XG-TW 3.05	Formula	PANTONE 2755 C XG-127 76.06 XG-230 16.19 XG-TW 6.59 XG-301 1.16	Formula
PANTONE 2765 C XG-127 74.00 XG-230 12.18 XG-TW 8.45 XG-301 5.37	Formula	PANTONE 2706 C XG-TW 98.94 XG-127 0.81 XG-230 0.25	Formula	PANTONE 2716 C XG-TW 95.53 XG-127 3.58 XG-230 0.89	Formula	PANTONE 2726 C XG-TW 74.15 XG-127 20.73 XG-230 5.12	Formula

Plastijet XG

PANTONE 2736 C XG-TW 61.10 XG-127 30.40 XG-230 8.50	Formula	PANTONE 2746 C XG-127 43.20 XG-TW 40.41 XG-230 15.76 XG-301 0.63	Formula	PANTONE 2756 C XG-127 47.90 XG-TW 35.60 XG-230 13.10 XG-301 3.40	Formula	PANTONE 2766 C XG-127 42.62 XG-TW 41.77 XG-230 8.05 XG-301 7.56	Formula
PANTONE 2707 C XG-TW 98.25 XG-127 1.05 XG-230 0.70	Formula	PANTONE 2717 C XG-TW 93.75 XG-127 3.75 XG-230 2.50	Formula	PANTONE 2727 C XG-TW 78.12 XG-230 12.50 XG-127 9.38	Formula	PANTONE Blue 072 C XG-127 47.54 XG-230 32.79 XG-MX 19.67	Formula
PANTONE 2747 C XG-230 58.65 XG-127 39.10 XG-301 2.25	Formula	PANTONE 2757 C XG-230 56.52 XG-127 37.68 XG-301 5.80	Formula	PANTONE 2767 C XG-230 50.00 XG-127 33.33 XG-301 16.67	Formula	PANTONE 2708 C XG-TW 96.12 XG-127 2.22 XG-230 1.48 XG-301 0.18	Formula
PANTONE 2718 C XG-TW 78.24 XG-127 13.20 XG-230 8.56	Formula	PANTONE 2728 C XG-MX 52.38 XG-127 28.57 XG-230 19.05	Formula	PANTONE 2738 C XG-127 61.50 XG-230 38.50	Formula	PANTONE 2748 C XG-230 52.63 XG-127 45.11 XG-301 2.26	Formula

Plastijet XG

PANTONE 2758 C XG-230 53.15 XG-127 41.95 XG-301 4.90	Formula	PANTONE 2768 C XG-230 49.35 XG-127 38.96 XG-301 11.69	Formula	PANTONE 277 C XG-TW 98.78 XG-127 0.62 XG-230 0.60	Formula	PANTONE 278 C XG-TW 69.15 XG-MX 27.92 XG-127 1.54 XG-230 1.39	Formula
PANTONE 279 C XG-TW 57.25 XG-MX 32.83 XG-230 5.98 XG-127 3.94	Formula	PANTONE Reflex Blue C XG-127 40.26 XG-TW 33.38 XG-230 26.36	Formula	PANTONE 280 C XG-230 66.53 XG-127 20.90 XG-TW 10.25 XG-301 2.32	Formula	PANTONE 281 C XG-230 61.53 XG-127 21.55 XG-TW 10.41 XG-301 6.51	Formula
PANTONE 282 C XG-230 59.16 XG-TW 18.63 XG-127 13.15 XG-301 9.06	Formula	PANTONE 283 C XG-TW 96.55 XG-230 2.07 XG-127 1.21 XG-301 0.17	Formula	PANTONE 284 C XG-TW 93.02 XG-230 4.65 XG-127 2.33	Formula	PANTONE 285 C XG-MX 40.65 XG-TW 32.52 XG-230 20.33 XG-127 6.50	Formula
PANTONE 286 C XG-230 54.90 XG-MX 28.80 XG-127 16.30	Formula	PANTONE 287 C XG-230 53.40 XG-MX 29.13 XG-127 15.53 XG-301 1.94	Formula	PANTONE 288 C XG-230 52.38 XG-MX 28.57 XG-127 15.24 XG-301 3.81	Formula	PANTONE 289 C XG-230 57.76 XG-MX 25.86 XG-301 13.79 XG-127 2.59	Formula

Plastijet XG

PANTONE 290 C XG-TW 98.71 XG-230 0.99 XG-127 0.30	Formula	PANTONE 291 C XG-TW 96.66 XG-230 2.42 XG-127 0.92	Formula	PANTONE 292 C XG-TW 92.59 XG-230 5.56 XG-127 1.85	Formula	PANTONE 293 C XG-230 60.13 XG-MX 33.33 XG-127 6.54	Formula
PANTONE 294 C XG-230 61.22 XG-MX 30.62 XG-127 6.12 XG-301 2.04	Formula	PANTONE 295 C XG-230 58.82 XG-MX 29.42 XG-127 5.88 XG-301 5.88	Formula	PANTONE 296 C XG-230 57.69 XG-MX 28.85 XG-301 13.46	Formula	PANTONE 2905 C XG-TW 97.09 XG-230 2.18 XG-127 0.73	Formula
PANTONE 2915 C XG-TW 91.26 XG-230 7.60 XG-127 1.14	Formula	PANTONE 2925 C XG-TW 81.97 XG-230 16.39 XG-127 1.64	Formula	PANTONE 2935 C XG-230 46.28 XG-MX 45.21 XG-127 8.51	Formula	PANTONE 2945 C XG-MX 47.17 XG-230 43.40 XG-127 7.55 XG-301 1.88	Formula
PANTONE 2955 C XG-MX 45.45 XG-230 41.82 XG-301 7.28 XG-127 5.45	Formula	PANTONE 2965 C XG-MX 39.06 XG-230 39.06 XG-301 18.75 XG-127 3.13	Formula	PANTONE 297 C XG-TW 97.09 XG-230 2.67 XG-127 0.24	Formula	PANTONE 298 C XG-TW 83.06 XG-MX 9.30 XG-230 7.31 XG-127 0.33	Formula

Plastijet XG

PANTONE 299 C XG-TW 70.18 XG-MX 16.37 XG-230 12.87 XG-127 0.58	Formula	PANTONE 300 C XG-MX 51.75 XG-230 43.86 XG-127 4.39	Formula	PANTONE 301 C XG-MX 49.50 XG-230 43.56 XG-127 3.96 XG-301 2.98	Formula	PANTONE 302 C XG-MX 46.73 XG-230 41.12 XG-301 8.41 XG-127 3.74	Formula
PANTONE 303 C XG-MX 43.48 XG-230 38.26 XG-301 14.78 XG-127 3.48	Formula	PANTONE 2975 C XG-TW 98.10 XG-230 1.54 XG-301 0.36	Formula	PANTONE 2985 C XG-TW 94.08 XG-230 5.38 XG-301 0.54	Formula	PANTONE 2995 C XG-TW 87.18 XG-230 12.82	Formula
PANTONE 3005 C XG-MX 66.47 XG-230 33.53	Formula	PANTONE 3015 C XG-MX 56.26 XG-230 42.19 XG-301 1.55	Formula	PANTONE 3025 C XG-230 50.00 XG-MX 40.00 XG-301 10.00	Formula	PANTONE 3035 C XG-230 44.64 XG-MX 22.32 XG-325 18.75 XG-301 14.29	Formula
PANTONE 304 C XG-TW 82.03 XG-MX 16.41 XG-230 1.15 XG-325 0.41	Formula	PANTONE 305 C XG-TW 80.00 XG-MX 15.24 XG-230 4.19 XG-325 0.57	Formula	PANTONE 306 C XG-TW 65.57 XG-MX 26.23 XG-230 7.22 XG-325 0.98	Formula	PANTONE Process Blue C XG-MX 77.74 XG-230 22.26	Formula

Plastijet XG

PANTONE 307 C XG-MX 75.27 XG-230 23.66 XG-301 1.07	Formula	PANTONE 308 C XG-MX 71.43 XG-230 22.45 XG-301 6.12	Formula	PANTONE 309 C XG-MX 64.22 XG-230 20.18 XG-301 12.85 XG-325 2.75	Formula	PANTONE 310 C XG-TW 75.14 XG-MX 20.23 XG-230 3.18 XG-325 1.45	Formula
PANTONE 311 C XG-TW 60.46 XG-MX 32.56 XG-230 5.12 XG-325 1.86	Formula	PANTONE 312 C XG-MX 56.00 XG-TW 32.00 XG-230 8.80 XG-325 3.20	Formula	PANTONE 313 C XG-MX 72.31 XG-230 22.73 XG-325 4.96	Formula	PANTONE 314 C XG-MX 70.71 XG-230 22.22 XG-325 5.05 XG-301 2.02	Formula
PANTONE 315 C XG-MX 67.96 XG-230 21.36 XG-301 5.83 XG-325 4.85	Formula	PANTONE 316 C XG-MX 61.40 XG-230 19.31 XG-301 11.40 XG-325 7.89	Formula	PANTONE 3105 C XG-TW 90.57 XG-MX 6.04 XG-230 2.01 XG-325 1.38	Formula	PANTONE 3115 C XG-TW 78.08 XG-MX 14.42 XG-230 4.80 XG-325 2.70	Formula
PANTONE 3125 C XG-TW 63.04 XG-MX 24.52 XG-230 8.06 XG-325 4.38	Formula	PANTONE 3135 C XG-MX 69.08 XG-230 21.26 XG-325 9.66	Formula	PANTONE 3145 C XG-MX 66.35 XG-230 22.12 XG-325 9.61 XG-301 1.92	Formula	PANTONE 3155 C XG-MX 64.49 XG-230 21.50 XG-325 9.34 XG-301 4.67	Formula

Plastijet XG

PANTONE 3165 C XG-MX 62.16 XG-230 20.72 XG-325 9.01 XG-301 8.11	Formula	PANTONE 317 C XG-MX 50.20 XG-TW 48.90 XG-325 0.70 XG-230 0.20	Formula	PANTONE 318 C XG-TW 67.30 XG-MX 30.60 XG-325 1.30 XG-230 0.80	Formula	PANTONE 319 C XG-MX 53.10 XG-TW 41.20 XG-325 3.00 XG-230 2.50 XG-301 0.20	Formula
PANTONE 320 C XG-MX 69.93 XG-230 16.30 XG-325 13.77	Formula	PANTONE 321 C XG-MX 64.20 XG-230 12.80 XG-325 12.80 XG-TW 8.40 XG-301 1.80	Formula	PANTONE 322 C XG-MX 47.50 XG-325 20.90 XG-230 14.90 XG-TW 13.80 XG-301 2.90	Formula	PANTONE 323 C XG-MX 63.80 XG-230 15.20 XG-325 12.80 XG-301 8.20	Formula
PANTONE 324 C XG-TW 63.20 XG-MX 35.30 XG-325 0.90 XG-230 0.50 XG-301 0.10	Formula	PANTONE 325 C XG-TW 84.40 XG-MX 10.60 XG-325 3.10 XG-230 1.60 XG-301 0.30	Formula	PANTONE 326 C XG-TW 59.70 XG-MX 27.50 XG-325 7.90 XG-230 4.10 XG-301 0.80	Formula	PANTONE 327 C XG-MX 57.81 XG-230 26.01 XG-064 11.56 XG-325 4.62	Formula
PANTONE 328 C XG-MX 36.40 XG-TW 25.60 XG-325 24.50 XG-230 10.30 XG-301 3.20	Formula	PANTONE 329 C XG-TW 32.50 XG-325 31.10 XG-MX 19.30 XG-230 13.00 XG-301 4.10	Formula	PANTONE 330 C XG-MX 55.30 XG-325 14.20 XG-301 11.60 XG-TW 11.20 XG-230 7.70	Formula	PANTONE 3242 C XG-TW 88.00 XG-MX 9.60 XG-325 1.80 XG-230 0.60	Formula

Plastijet XG

PANTONE 3252 C XG-TW 76.00 XG-MX 19.20 XG-325 3.70 XG-230 1.10	Formula	PANTONE 3262 C XG-TW 46.40 XG-MX 42.90 XG-325 8.30 XG-230 2.40	Formula	PANTONE 3272 C XG-MX 73.08 XG-325 19.23 XG-230 7.69	Formula	PANTONE 3282 C XG-MX 66.50 XG-325 23.30 XG-230 7.10 XG-301 3.10	Formula
PANTONE 3292 C XG-MX 45.60 XG-325 34.90 XG-301 10.70 XG-230 8.80	Formula	PANTONE 3302 C XG-325 50.00 XG-MX 21.82 XG-301 15.45 XG-230 12.73	Formula	PANTONE 3245 C XG-TW 95.43 XG-325 3.47 XG-230 0.81 XG-064 0.29	Formula	PANTONE 3255 C XG-TW 78.43 XG-MX 12.07 XG-325 7.24 XG-230 1.66 XG-064 0.60	Formula
PANTONE 3265 C XG-TW 66.19 XG-MX 18.91 XG-325 11.35 XG-230 2.60 XG-064 0.95	Formula	PANTONE 3275 C XG-MX 51.12 XG-TW 22.43 XG-325 21.52 XG-230 4.93	Formula	PANTONE 3285 C XG-TW 68.78 XG-325 24.04 XG-MX 4.58 XG-230 1.33 XG-301 1.27	Formula	PANTONE 3295 C XG-325 48.00 XG-TW 40.00 XG-230 11.00 XG-301 1.00	Formula
PANTONE 3305 C XG-325 57.14 XG-MX 23.82 XG-301 10.71 XG-TW 4.76 XG-230 3.57	Formula	PANTONE 3248 C XG-TW 96.65 XG-325 2.81 XG-230 0.54	Formula	PANTONE 3258 C XG-TW 92.60 XG-325 6.26 XG-230 1.14	Formula	PANTONE 3268 C XG-TW 80.42 XG-325 16.88 XG-230 2.70	Formula

Plastijet XG

PANTONE 3278 C XG-TW 56.30 XG-325 42.40 XG-230 1.30	Formula	PANTONE 3288 C XG-TW 54.53 XG-325 42.05 XG-301 2.39 XG-230 1.03	Formula	PANTONE 3298 C XG-325 50.59 XG-TW 43.96 XG-301 5.18 XG-230 0.27	Formula	PANTONE 3308 C XG-230 42.90 XG-066 30.80 XG-TW 23.90 XG-301 2.40	Formula
PANTONE 331 C XG-TW 98.60 XG-325 1.23 XG-064 0.17	Formula	PANTONE 332 C XG-TW 97.03 XG-325 2.67 XG-301 0.20 XG-230 0.10	Formula	PANTONE 333 C XG-TW 72.99 XG-MX 13.69 XG-325 12.77 XG-230 0.55	Formula	PANTONE Green C XG-MX 53.06 XG-325 28.57 XG-TW 17.35 XG-230 1.02	Formula
PANTONE 334 C XG-MX 57.14 XG-325 39.18 XG-230 2.04 XG-301 1.64	Formula	PANTONE 335 C XG-MX 55.78 XG-325 38.25 XG-301 3.98 XG-230 1.99	Formula	PANTONE 336 C XG-MX 54.90 XG-325 35.29 XG-301 7.85 XG-230 1.96	Formula	PANTONE 337 C XG-TW 95.74 XG-325 3.72 XG-064 0.27 XG-301 0.27	Formula
PANTONE 338 C XG-TW 90.91 XG-325 7.95 XG-064 0.57 XG-301 0.57	Formula	PANTONE 339 C XG-TW 68.63 XG-325 29.41 XG-064 0.98 XG-230 0.98	Formula	PANTONE 340 C XG-325 60.24 XG-MX 37.69 XG-230 2.07	Formula	PANTONE 341 C XG-325 70.59 XG-MX 23.53 XG-301 3.53 XG-230 2.35	Formula

Plastijet XG

PANTONE 342 C XG-325 68.18 XG-MX 22.73 XG-301 6.82 XG-230 2.27	Formula	PANTONE 343 C XG-325 63.83 XG-MX 21.28 XG-301 12.77 XG-230 2.12	Formula	PANTONE 3375 C XG-TW 90.21 XG-325 4.41 XG-MX 3.84 XG-064 1.54	Formula	PANTONE 3385 C XG-TW 84.55 XG-325 6.68 XG-MX 6.26 XG-064 2.51	Formula
PANTONE 3395 C XG-TW 62.63 XG-325 16.16 XG-MX 15.15 XG-064 6.06	Formula	PANTONE 3405 C XG-TW 37.29 XG-325 27.12 XG-MX 25.42 XG-064 10.17	Formula	PANTONE 3415 C XG-TW 48.00 XG-325 36.00 XG-064 13.33 XG-301 2.67	Formula	PANTONE 3425 C XG-TW 42.86 XG-325 34.52 XG-064 16.67 XG-301 5.95	Formula
PANTONE 3435 C XG-325 33.64 XG-TW 32.72 XG-064 23.64 XG-301 10.00	Formula	PANTONE 344 C XG-TW 97.16 XG-064 2.11 XG-230 0.73	Formula	PANTONE 345 C XG-TW 94.05 XG-064 4.32 XG-230 1.63	Formula	PANTONE 346 C XG-TW 73.11 XG-MX 18.18 XG-064 6.15 XG-230 2.33 XG-325 0.23	Formula
PANTONE 347 C XG-325 37.08 XG-TW 35.87 XG-064 27.05	Formula	PANTONE 348 C XG-325 36.82 XG-064 33.84 XG-TW 28.36 XG-301 0.98	Formula	PANTONE 349 C XG-064 37.60 XG-325 30.38 XG-TW 27.09 XG-301 4.93	Formula	PANTONE 350 C XG-066 43.50 XG-TW 26.30 XG-230 20.25 XG-165 9.95	Formula

Plastijet XG

PANTONE 351 C XG-TW 96.90 XG-064 1.55 XG-325 1.55	Formula	PANTONE 352 C XG-TW 92.60 XG-064 2.70 XG-MX 2.60 XG-325 2.10	Formula	PANTONE 353 C XG-TW 85.80 XG-064 5.20 XG-MX 5.10 XG-325 3.90	Formula	PANTONE 354 C XG-064 39.25 XG-MX 28.04 XG-325 27.10 XG-TW 5.61	Formula
PANTONE 355 C XG-064 35.80 XG-MX 35.00 XG-325 27.00 XG-301 2.20	Formula	PANTONE 356 C XG-MX 55.40 XG-064 20.00 XG-325 17.80 XG-301 6.80	Formula	PANTONE 357 C XG-MX 46.73 XG-064 24.30 XG-325 16.82 XG-301 12.15	Formula	PANTONE 358 C XG-TW 89.32 XG-064 9.52 XG-230 1.16	Formula
PANTONE 359 C XG-TW 87.65 XG-064 11.09 XG-230 1.26	Formula	PANTONE 360 C XG-TW 64.10 XG-064 33.22 XG-230 2.68	Formula	PANTONE 361 C XG-064 58.50 XG-TW 32.31 XG-325 4.94 XG-230 4.25	Formula	PANTONE 362 C XG-064 61.23 XG-TW 33.30 XG-230 4.63 XG-301 0.56 XG-325 0.28	Formula
PANTONE 363 C XG-064 74.16 XG-TW 17.71 XG-230 5.85 XG-301 2.28	Formula	PANTONE 364 C XG-064 75.54 XG-TW 15.17 XG-230 5.16 XG-301 4.13	Formula	PANTONE 365 C XG-TW 94.22 XG-064 5.43 XG-230 0.35	Formula	PANTONE 366 C XG-TW 90.07 XG-064 9.34 XG-230 0.59	Formula

Plastijet XG

PANTONE 367 C XG-TW 75.76 XG-064 22.92 XG-230 1.01 XG-325 0.31	Formula	PANTONE 368 C XG-064 71.76 XG-TW 24.90 XG-230 2.47 XG-325 0.87	Formula	PANTONE 369 C XG-064 80.73 XG-TW 15.33 XG-230 3.48 XG-301 0.46	Formula	PANTONE 370 C XG-064 84.35 XG-TW 10.03 XG-230 3.62 XG-301 2.00	Formula
PANTONE 371 C XG-064 78.68 XG-TW 9.27 XG-301 8.93 XG-230 3.12	Formula	PANTONE 372 C XG-TW 93.40 XG-064 6.30 XG-325 0.30	Formula	PANTONE 373 C XG-TW 82.50 XG-064 16.80 XG-325 0.70	Formula	PANTONE 374 C XG-TW 63.50 XG-064 35.00 XG-325 1.50	Formula
PANTONE 375 C XG-064 96.13 XG-325 3.87	Formula	PANTONE 376 C XG-064 94.40 XG-325 4.40 XG-301 1.20	Formula	PANTONE 377 C XG-064 92.10 XG-325 4.00 XG-301 3.90	Formula	PANTONE 378 C XG-064 86.70 XG-301 10.00 XG-325 3.30	Formula
PANTONE 379 C XG-TW 77.36 XG-064 22.42 XG-230 0.22	Formula	PANTONE 380 C XG-064 54.47 XG-TW 45.09 XG-230 0.44	Formula	PANTONE 381 C XG-064 54.30 XG-TW 45.10 XG-230 0.40 XG-325 0.20	Formula	PANTONE 382 C XG-064 81.50 XG-TW 17.30 XG-325 0.80 XG-230 0.40	Formula

Plastijet XG

PANTONE 383 C XG-064 96.88 XG-301 1.33 XG-230 0.97 XG-TW 0.82	Formula	PANTONE 384 C XG-064 96.22 XG-301 2.66 XG-230 0.83 XG-TW 0.29	Formula	PANTONE 385 C XG-064 91.15 XG-301 8.11 XG-TW 0.64 XG-230 0.10	Formula	PANTONE 386 C XG-TW 65.29 XG-064 34.36 XG-325 0.35	Formula
PANTONE 387 C XG-064 52.36 XG-TW 47.12 XG-325 0.52	Formula	PANTONE 388 C XG-064 82.64 XG-TW 16.53 XG-325 0.83	Formula	PANTONE 389 C XG-064 99.00 XG-325 1.00	Formula	PANTONE 390 C XG-064 98.04 XG-325 0.98 XG-301 0.98	Formula
PANTONE 391 C XG-064 96.62 XG-301 1.93 XG-325 0.97 XG-121 0.48	Formula	PANTONE 392 C XG-064 95.15 XG-301 3.53 XG-325 0.88 XG-121 0.44	Formula	PANTONE 393 C XG-TW 85.62 XG-064 14.26 XG-325 0.12	Formula	PANTONE 394 C XG-TW 66.55 XG-064 33.28 XG-325 0.17	Formula
PANTONE 395 C XG-TW 76.60 XG-064 23.00 XG-325 0.40	Formula	PANTONE 396 C XG-064 99.61 XG-325 0.39	Formula	PANTONE 397 C XG-064 98.52 XG-301 0.99 XG-325 0.49	Formula	PANTONE 398 C XG-064 97.56 XG-301 2.03 XG-325 0.41	Formula

Plastijet XG

PANTONE 399 C XG-064 96.78 XG-301 2.82 XG-325 0.40	Formula	PANTONE 3935 C XG-TW 68.24 XG-064 31.66 XG-230 0.10	Formula	PANTONE 3945 C XG-TW 86.55 XG-064 13.32 XG-230 0.13	Formula	PANTONE 3955 C XG-064 99.80 XG-230 0.20	Formula
PANTONE 3965 C XG-064 99.70 XG-230 0.30	Formula	PANTONE 3975 C XG-064 98.04 XG-301 1.96	Formula	PANTONE 3985 C XG-064 96.62 XG-301 3.38	Formula	PANTONE 3995 C XG-064 91.32 XG-301 7.31 XG-121 1.37	Formula
PANTONE 400 C XG-TW 98.23 XG-301 1.06 XG-066 0.40 XG-165 0.31	Formula	PANTONE 401 C XG-TW 97.08 XG-301 1.73 XG-066 0.67 XG-165 0.52	Formula	PANTONE 402 C XG-TW 94.95 XG-301 2.87 XG-066 1.28 XG-165 0.90	Formula	PANTONE 403 C XG-TW 89.86 XG-301 5.56 XG-066 2.66 XG-165 1.92	Formula
PANTONE 404 C XG-TW 82.67 XG-301 7.86 XG-066 5.58 XG-165 3.89	Formula	PANTONE 405 C XG-TW 71.28 XG-301 11.05 XG-066 10.35 XG-165 7.32	Formula	PANTONE Black C XG-TW 48.73 XG-301 18.87 XG-066 16.70 XG-165 15.70	Formula	PANTONE 406 C XG-TW 98.04 XG-301 1.23 XG-066 0.53 XG-164 0.20	Formula

Plastijet XG

PANTONE 407 C XG-TW 96.28 XG-301 2.32 XG-066 0.96 XG-164 0.44	Formula	PANTONE 408 C XG-TW 94.33 XG-301 3.39 XG-066 1.54 XG-164 0.74	Formula	PANTONE 409 C XG-TW 91.28 XG-301 4.94 XG-066 2.54 XG-164 1.24	Formula	PANTONE 410 C XG-TW 84.38 XG-301 7.61 XG-066 5.44 XG-164 2.57	Formula
PANTONE 411 C XG-TW 76.78 XG-301 10.64 XG-066 8.39 XG-164 4.19	Formula	PANTONE 412 C XG-TW 41.66 XG-165 22.92 XG-301 18.45 XG-066 16.97	Formula	PANTONE 413 C XG-TW 97.17 XG-301 2.02 XG-066 0.81	Formula	PANTONE 414 C XG-TW 95.76 XG-301 3.01 XG-066 1.23	Formula
PANTONE 415 C XG-TW 93.24 XG-301 4.66 XG-066 2.10	Formula	PANTONE 416 C XG-TW 91.74 XG-301 6.29 XG-066 1.97	Formula	PANTONE 417 C XG-TW 84.98 XG-301 9.81 XG-066 5.21	Formula	PANTONE 418 C XG-TW 77.48 XG-301 13.90 XG-066 8.62	Formula
PANTONE 419 C XG-301 46.72 XG-TW 27.37 XG-114 25.91	Formula	PANTONE 420 C XG-TW 98.67 XG-301 0.95 XG-064 0.38	Formula	PANTONE 421 C XG-TW 97.24 XG-301 2.10 XG-064 0.66	Formula	PANTONE 422 C XG-TW 96.06 XG-301 2.98 XG-064 0.96	Formula

Plastijet XG

PANTONE 423 C XG-TW 91.70 XG-301 5.56 XG-064 2.14 XG-127 0.60	Formula	PANTONE 424 C XG-TW 85.09 XG-301 7.44 XG-064 5.07 XG-127 2.40	Formula	PANTONE 425 C XG-TW 70.82 XG-064 12.06 XG-301 11.33 XG-127 5.79	Formula	PANTONE 426 C XG-TW 48.53 XG-301 22.66 XG-127 14.94 XG-066 13.87	Formula
PANTONE 427 C XG-TW 99.10 XG-127 0.42 XG-066 0.24 XG-230 0.14 XG-301 0.10	Formula	PANTONE 428 C XG-TW 97.94 XG-127 0.97 XG-066 0.50 XG-230 0.30 XG-301 0.29	Formula	PANTONE 429 C XG-TW 95.40 XG-127 1.98 XG-066 1.09 XG-301 0.91 XG-230 0.62	Formula	PANTONE 430 C XG-TW 90.03 XG-127 5.53 XG-066 3.02 XG-230 1.42	Formula
PANTONE 431 C XG-TW 79.25 XG-127 11.44 XG-066 6.34 XG-230 2.97	Formula	PANTONE 432 C XG-TW 46.83 XG-064 24.24 XG-127 20.16 XG-230 4.91 XG-301 3.86	Formula	PANTONE 433 C XG-127 39.28 XG-TW 31.40 XG-066 17.81 XG-230 11.51	Formula	PANTONE 434 C XG-TW 98.77 XG-301 0.80 XG-121 0.23 XG-114 0.20	Formula
PANTONE 435 C XG-TW 97.97 XG-301 1.25 XG-121 0.47 XG-114 0.31	Formula	PANTONE 436 C XG-TW 95.80 XG-301 2.50 XG-121 1.10 XG-114 0.60	Formula	PANTONE 437 C XG-TW 88.81 XG-301 6.91 XG-114 2.56 XG-121 1.72	Formula	PANTONE 438 C XG-TW 58.09 XG-301 20.62 XG-114 14.32 XG-121 6.97	Formula

Plastijet XG

PANTONE 439 C XG-TW 49.65 XG-301 28.51 XG-114 14.28 XG-121 7.56	Formula	PANTONE 440 C XG-301 36.30 XG-TW 32.50 XG-121 18.60 XG-114 12.60	Formula	PANTONE 441 C XG-TW 97.78 XG-121 1.00 XG-325 0.93 XG-114 0.29	Formula	PANTONE 442 C XG-TW 96.01 XG-121 1.88 XG-325 1.66 XG-114 0.45	Formula
PANTONE 443 C XG-TW 92.64 XG-121 3.54 XG-325 3.02 XG-114 0.80	Formula	PANTONE 444 C XG-TW 86.35 XG-121 6.57 XG-325 5.64 XG-114 1.44	Formula	PANTONE 445 C XG-TW 46.18 XG-MX 18.86 XG-165 16.30 XG-325 12.23 XG-114 6.43	Formula	PANTONE 446 C XG-TW 43.76 XG-165 23.46 XG-325 19.61 XG-114 13.17	Formula
PANTONE 447 C XG-TW 37.06 XG-165 25.36 XG-325 21.28 XG-114 16.30	Formula	PANTONE WARM GRAY 1 C XG-TW 98.96 XG-301 0.49 XG-066 0.32 XG-165 0.23	Formula	PANTONE WARM GRAY 2 C XG-TW 98.20 XG-301 0.96 XG-066 0.44 XG-165 0.40	Formula	PANTONE WARM GRAY 3 C XG-TW 96.02 XG-301 2.25 XG-165 0.89 XG-066 0.84	Formula
PANTONE WARM GRAY 4 C XG-TW 96.24 XG-301 2.00 XG-165 0.88 XG-066 0.88	Formula	PANTONE WARM GRAY 5 C XG-TW 94.86 XG-301 2.67 XG-066 1.32 XG-165 1.15	Formula	PANTONE WARM GRAY 6 C XG-TW 94.33 XG-301 2.89 XG-066 1.51 XG-165 1.27	Formula	PANTONE WARM GRAY 7 C XG-TW 93.00 XG-301 3.45 XG-066 1.92 XG-165 1.63	Formula

Plastijet XG

PANTONE WARM GRAY 8 C XG-TW 90.49 XG-301 4.73 XG-066 2.52 XG-165 2.26	Formula	PANTONE WARM GRAY 9 C XG-TW 86.45 XG-301 5.92 XG-066 4.02 XG-165 3.61	Formula	PANTONE WARM GRAY 10 C XG-TW 81.11 XG-301 7.97 XG-066 5.85 XG-165 5.07	Formula	PANTONE WARM GRAY 11 C XG-TW 70.20 XG-301 11.23 XG-066 9.99 XG-165 8.58	Formula
PANTONE COOL GRAY 1 C XG-TW 99.49 XG-301 0.51	Formula	PANTONE COOL GRAY 2 C XG-TW 98.51 XG-301 1.38 XG-064 0.11	Formula	PANTONE COOL GRAY 3 C XG-TW 98.18 XG-301 1.68 XG-064 0.14	Formula	PANTONE COOL GRAY 4 C XG-TW 97.65 XG-301 2.17 XG-064 0.18	Formula
PANTONE COOL GRAY 5 C XG-TW 96.69 XG-301 3.00 XG-064 0.21 XG-114 0.10	Formula	PANTONE COOL GRAY 6 C XG-TW 96.52 XG-301 3.14 XG-064 0.22 XG-114 0.12	Formula	PANTONE COOL GRAY 7 C XG-TW 95.54 XG-301 4.00 XG-064 0.30 XG-114 0.16	Formula	PANTONE COOL GRAY 8 C XG-TW 95.10 XG-301 4.40 XG-064 0.32 XG-114 0.18	Formula
PANTONE COOL GRAY 9 C XG-TW 89.23 XG-301 9.65 XG-064 0.72 XG-114 0.40	Formula	PANTONE COOL GRAY 10 C XG-TW 84.58 XG-301 13.32 XG-064 1.35 XG-114 0.75	Formula	PANTONE COOL GRAY 11 C XG-TW 83.26 XG-301 15.00 XG-064 1.12 XG-114 0.62	Formula	PANTONE 448 C XG-MX 59.20 XG-TW 19.00 XG-301 13.77 XG-066 7.10 XG-164 0.93	Formula

Plastijet XG

PANTONE 449 C XG-MX 49.66 XG-TW 20.22 XG-066 16.85 XG-301 12.50 XG-164 0.77	Formula	PANTONE 450 C XG-MX 45.52 XG-TW 28.19 XG-066 14.73 XG-301 10.86 XG-164 0.70	Formula	PANTONE 451 C XG-TW 66.90 XG-MX 18.56 XG-064 11.35 XG-164 2.06 XG-230 1.13	Formula	PANTONE 452 C XG-TW 73.83 XG-MX 18.48 XG-064 5.88 XG-164 1.16 XG-230 0.65	Formula
PANTONE 453 C XG-TW 96.33 XG-064 2.80 XG-164 0.57 XG-230 0.30	Formula	PANTONE 454 C XG-TW 97.75 XG-064 1.75 XG-164 0.34 XG-230 0.16	Formula	PANTONE 4485 C XG-TW 38.07 XG-066 25.70 XG-MX 23.88 XG-301 10.50 XG-164 1.85	Formula	PANTONE 4495 C XG-TW 65.85 XG-066 26.96 XG-301 6.43 XG-164 0.76	Formula
PANTONE 4505 C XG-TW 64.23 XG-064 30.93 XG-301 3.48 XG-164 1.36	Formula	PANTONE 4515 C XG-TW 85.23 XG-064 12.22 XG-301 1.90 XG-164 0.65	Formula	PANTONE 4525 C XG-TW 91.11 XG-064 7.17 XG-301 1.24 XG-164 0.48	Formula	PANTONE 4535 C XG-TW 95.73 XG-064 3.46 XG-301 0.58 XG-164 0.23	Formula
PANTONE 4545 C XG-TW 97.35 XG-064 2.16 XG-301 0.33 XG-164 0.16	Formula	PANTONE 455 C XG-064 77.12 XG-164 11.58 XG-325 11.30	Formula	PANTONE 456 C XG-064 90.92 XG-164 4.60 XG-325 4.48	Formula	PANTONE 457 C XG-064 93.09 XG-164 3.72 XG-325 3.19	Formula

Plastijet XG

PANTONE 458 C XG-TW 79.90 XG-064 18.70 XG-164 0.90 XG-325 0.50	Formula	PANTONE 459 C XG-TW 88.17 XG-064 10.86 XG-164 0.62 XG-325 0.35	Formula	PANTONE 460 C XG-TW 93.08 XG-064 6.36 XG-164 0.36 XG-325 0.20	Formula	PANTONE 461 C XG-TW 96.03 XG-064 3.65 XG-164 0.21 XG-325 0.11	Formula
PANTONE 462 C XG-064 72.91 XG-301 11.29 XG-TW 9.49 XG-164 6.31	Formula	PANTONE 463 C XG-064 74.45 XG-TW 12.29 XG-301 7.75 XG-164 5.51	Formula	PANTONE 464 C XG-064 76.05 XG-TW 11.87 XG-127 7.06 XG-164 2.86 XG-301 2.16	Formula	PANTONE 465 C XG-TW 82.95 XG-064 13.79 XG-127 2.71 XG-164 0.55	Formula
PANTONE 466 C XG-TW 90.47 XG-064 7.45 XG-127 1.77 XG-164 0.31	Formula	PANTONE 467 C XG-TW 93.08 XG-064 5.34 XG-127 1.35 XG-164 0.23	Formula	PANTONE 468 C XG-TW 95.78 XG-064 3.27 XG-127 0.77 XG-164 0.18	Formula	PANTONE 4625 C XG-114 36.75 XG-165 35.54 XG-301 16.42 XG-TW 11.29	Formula
PANTONE 4635 C XG-TW 52.16 XG-066 26.38 XG-121 15.25 XG-301 6.21	Formula	PANTONE 4645 C XG-TW 83.63 XG-066 7.05 XG-121 6.44 XG-301 2.88	Formula	PANTONE 4655 C XG-TW 91.20 XG-121 3.60 XG-066 3.40 XG-301 1.80	Formula	PANTONE 4665 C XG-TW 95.62 XG-121 1.87 XG-066 1.60 XG-301 0.91	Formula

Plastijet XG

PANTONE 4675 C XG-TW 97.44 XG-121 1.16 XG-066 0.89 XG-301 0.51	Formula	PANTONE 4685 C XG-TW 98.80 XG-121 0.55 XG-066 0.46 XG-301 0.19	Formula	PANTONE 469 C XG-114 52.81 XG-TW 25.43 XG-301 11.31 XG-165 10.45	Formula	PANTONE 470 C XG-TW 52.83 XG-114 42.30 XG-301 4.87	Formula
PANTONE 471 C XG-TW 59.93 XG-114 37.23 XG-301 2.84	Formula	PANTONE 472 C XG-TW 92.74 XG-064 3.12 XG-114 3.06 XG-127 1.08	Formula	PANTONE 473 C XG-TW 96.73 XG-114 1.48 XG-064 1.24 XG-127 0.55	Formula	PANTONE 474 C XG-TW 97.95 XG-114 0.90 XG-064 0.77 XG-127 0.38	Formula
PANTONE 475 C XG-TW 98.68 XG-114 0.68 XG-064 0.47 XG-127 0.17	Formula	PANTONE 4695 C XG-066 37.59 XG-165 35.01 XG-TW 15.45 XG-301 11.95	Formula	PANTONE 4705 C XG-TW 61.89 XG-066 21.33 XG-164 10.15 XG-301 6.63	Formula	PANTONE 4715 C XG-TW 82.60 XG-066 8.40 XG-164 4.70 XG-301 4.30	Formula
PANTONE 4725 C XG-TW 91.40 XG-066 3.70 XG-301 2.50 XG-164 2.40	Formula	PANTONE 4735 C XG-TW 96.26 XG-066 1.48 XG-301 1.25 XG-164 1.01	Formula	PANTONE 4745 C XG-TW 97.50 XG-066 0.93 XG-301 0.93 XG-164 0.64	Formula	PANTONE 4755 C XG-TW 98.73 XG-066 0.51 XG-301 0.42 XG-164 0.34	Formula

Plastijet XG

PANTONE 476 C XG-064 30.54 XG-165 20.22 XG-MX 19.29 XG-TW 19.06 XG-301 10.89	Formula	PANTONE 477 C XG-064 42.63 XG-165 34.44 XG-TW 12.68 XG-301 10.25	Formula	PANTONE 478 C XG-064 41.95 XG-165 34.97 XG-TW 14.95 XG-301 8.13	Formula	PANTONE 479 C XG-TW 78.89 XG-064 14.63 XG-127 4.55 XG-164 1.93	Formula
PANTONE 480 C XG-TW 92.42 XG-064 5.03 XG-127 1.90 XG-164 0.65	Formula	PANTONE 481 C XG-TW 96.88 XG-064 2.04 XG-127 0.82 XG-164 0.26	Formula	PANTONE 482 C XG-TW 97.36 XG-064 1.76 XG-127 0.65 XG-164 0.23	Formula	PANTONE 483 C XG-121 60.92 XG-MX 24.54 XG-325 7.47 XG-165 4.11 XG-TW 2.96	Formula
PANTONE 484 C XG-121 70.38 XG-165 10.27 XG-MX 10.26 XG-TW 6.15 XG-325 2.94	Formula	PANTONE 485 C XG-066 75.98 XG-164 21.95 XG-TW 2.07	Formula	PANTONE 486 C XG-TW 88.26 XG-064 8.73 XG-164 3.01	Formula	PANTONE 487 C XG-TW 93.35 XG-064 5.02 XG-164 1.63	Formula
PANTONE 488 C XG-TW 96.42 XG-064 2.62 XG-164 0.96	Formula	PANTONE 489 C XG-TW 97.69 XG-064 1.69 XG-164 0.62	Formula	PANTONE 490 C XG-165 45.29 XG-TW 25.78 XG-114 21.70 XG-301 3.85 XG-230 3.38	Formula	PANTONE 491 C XG-165 47.11 XG-TW 26.80 XG-114 22.58 XG-230 3.51	Formula

Plastijet XG

PANTONE 492 C XG-TW 46.19 XG-165 36.08 XG-114 15.80 XG-230 1.93	Formula	PANTONE 493 C XG-TW 89.17 XG-121 9.23 XG-114 1.09 XG-230 0.51	Formula	PANTONE 494 C XG-TW 94.95 XG-121 4.00 XG-064 0.80 XG-230 0.25	Formula	PANTONE 495 C XG-TW 97.01 XG-121 2.40 XG-064 0.42 XG-230 0.17	Formula
PANTONE 496 C XG-TW 97.30 XG-121 2.15 XG-064 0.43 XG-230 0.12	Formula	PANTONE 497 C XG-165 42.91 XG-114 23.98 XG-TW 20.98 XG-325 8.28 XG-301 3.85	Formula	PANTONE 498 C XG-165 44.62 XG-114 24.94 XG-TW 21.82 XG-325 8.62	Formula	PANTONE 499 C XG-165 39.45 XG-114 25.73 XG-TW 25.72 XG-301 7.38 XG-325 1.72	Formula
PANTONE 500 C XG-TW 87.40 XG-121 9.60 XG-114 1.70 XG-325 1.30	Formula	PANTONE 501 C XG-TW 95.37 XG-121 3.45 XG-301 0.74 XG-066 0.44	Formula	PANTONE 502 C XG-TW 97.50 XG-121 1.85 XG-301 0.40 XG-066 0.25	Formula	PANTONE 503 C XG-TW 98.67 XG-121 0.99 XG-301 0.21 XG-066 0.13	Formula
PANTONE 4975 C XG-121 36.38 XG-165 25.79 XG-301 20.21 XG-TW 12.34 XG-066 5.28	Formula	PANTONE 4985 C XG-TW 59.31 XG-121 25.95 XG-301 9.67 XG-066 5.07	Formula	PANTONE 4995 C XG-TW 80.45 XG-121 13.37 XG-301 4.95 XG-066 1.23	Formula	PANTONE 5005 C XG-TW 88.50 XG-121 7.08 XG-301 3.54 XG-066 0.88	Formula

Plastijet XG

PANTONE 5015 C XG-TW 94.70 XG-121 3.27 XG-301 1.62 XG-066 0.41	Formula	PANTONE 5025 C XG-TW 97.14 XG-121 1.77 XG-301 0.87 XG-066 0.22	Formula	PANTONE 5035 C XG-TW 98.48 XG-121 0.94 XG-301 0.46 XG-066 0.12	Formula	PANTONE 504 C XG-165 45.48 XG-121 35.48 XG-301 11.79 XG-325 7.25	Formula
PANTONE 505 C XG-165 51.56 XG-121 40.23 XG-325 8.21	Formula	PANTONE 506 C XG-165 39.15 XG-121 37.57 XG-TW 16.14 XG-325 7.14	Formula	PANTONE 507 C XG-TW 88.62 XG-121 8.05 XG-165 2.42 XG-325 0.91	Formula	PANTONE 508 C XG-TW 93.68 XG-121 4.47 XG-165 1.35 XG-325 0.50	Formula
PANTONE 509 C XG-TW 96.57 XG-121 2.43 XG-165 0.73 XG-325 0.27	Formula	PANTONE 510 C XG-TW 98.15 XG-121 1.30 XG-165 0.40 XG-325 0.15	Formula	PANTONE 511 C XG-165 48.20 XG-MX 32.40 XG-301 9.30 XG-121 6.70 XG-325 3.40	Formula	PANTONE 512 C XG-165 49.18 XG-MX 33.00 XG-TW 12.56 XG-301 3.30 XG-325 1.96	Formula
PANTONE 513 C XG-165 50.68 XG-MX 34.03 XG-TW 12.95 XG-325 2.34	Formula	PANTONE 514 C XG-TW 87.08 XG-165 11.17 XG-121 1.30 XG-325 0.45	Formula	PANTONE 515 C XG-TW 93.83 XG-165 5.17 XG-121 0.81 XG-325 0.19	Formula	PANTONE 516 C XG-TW 96.56 XG-165 2.50 XG-121 0.84 XG-325 0.10	Formula

Plastijet XG

PANTONE 517 C XG-TW 98.15 XG-165 1.20 XG-121 0.65	Formula	PANTONE 5115 C XG-165 51.24 XG-TW 28.61 XG-301 12.14 XG-064 8.01	Formula	PANTONE 5125 C XG-TW 56.87 XG-165 32.22 XG-301 8.22 XG-064 2.69	Formula	PANTONE 5135 C XG-TW 77.90 XG-165 15.43 XG-301 4.68 XG-064 1.99	Formula
PANTONE 5145 C XG-TW 93.99 XG-301 2.74 XG-164 2.67 XG-064 0.60	Formula	PANTONE 5155 C XG-TW 97.68 XG-301 1.16 XG-164 0.90 XG-064 0.26	Formula	PANTONE 5165 C XG-TW 99.03 XG-301 0.49 XG-164 0.35 XG-064 0.13	Formula	PANTONE 5175 C XG-TW 99.30 XG-301 0.30 XG-164 0.24 XG-064 0.16	Formula
PANTONE 518 C XG-165 54.59 XG-TW 24.50 XG-064 9.27 XG-301 8.59 XG-230 3.05	Formula	PANTONE 519 C XG-165 63.50 XG-TW 18.40 XG-064 10.30 XG-230 5.80 XG-301 2.00	Formula	PANTONE 520 C XG-165 63.70 XG-TW 24.50 XG-064 5.50 XG-230 5.20 XG-301 1.10	Formula	PANTONE 521 C XG-TW 85.61 XG-165 11.41 XG-064 1.81 XG-230 1.17	Formula
PANTONE 522 C XG-TW 91.60 XG-165 6.52 XG-064 1.19 XG-230 0.69	Formula	PANTONE 523 C XG-TW 95.31 XG-165 3.55 XG-064 0.79 XG-230 0.35	Formula	PANTONE 524 C XG-TW 97.41 XG-165 1.90 XG-064 0.43 XG-230 0.26	Formula	PANTONE 5185 C XG-121 56.54 XG-127 31.38 XG-230 12.08	Formula

Plastijet XG

PANTONE 5195 C XG-165 42.96 XG-TW 39.16 XG-301 13.14 XG-114 4.74	Formula	PANTONE 5205 C XG-TW 76.84 XG-165 14.45 XG-301 6.37 XG-114 2.34	Formula	PANTONE 5215 C XG-TW 91.31 XG-165 4.68 XG-301 3.19 XG-114 0.82	Formula	PANTONE 5225 C XG-TW 95.91 XG-165 1.99 XG-301 1.66 XG-114 0.44	Formula
PANTONE 5235 C XG-TW 98.47 XG-165 0.74 XG-301 0.61 XG-114 0.18	Formula	PANTONE 5245 C XG-TW 98.94 XG-165 0.48 XG-301 0.46 XG-114 0.12	Formula	PANTONE 525 C XG-165 45.56 XG-TW 29.85 XG-127 16.96 XG-301 7.63	Formula	PANTONE 526 C XG-165 30.32 XG-TW 25.78 XG-127 22.52 XG-MX 19.35 XG-301 2.03	Formula
PANTONE 527 C XG-TW 34.37 XG-165 23.15 XG-127 22.30 XG-MX 20.18	Formula	PANTONE 528 C XG-TW 83.20 XG-165 10.18 XG-127 6.62	Formula	PANTONE 529 C XG-TW 94.59 XG-127 2.94 XG-165 2.47	Formula	PANTONE 530 C XG-TW 96.79 XG-127 1.91 XG-165 1.30	Formula
PANTONE 531 C XG-TW 98.14 XG-127 1.07 XG-165 0.79	Formula	PANTONE 5255 C XG-127 58.73 XG-TW 25.40 XG-301 15.87	Formula	PANTONE 5265 C XG-TW 46.79 XG-127 37.38 XG-301 14.01 XG-230 1.82	Formula	PANTONE 5275 C XG-TW 63.56 XG-127 23.89 XG-301 11.27 XG-230 1.28	Formula

Plastijet XG

PANTONE 5285 C XG-TW 86.55 XG-127 8.40 XG-301 4.60 XG-230 0.45	Formula	PANTONE 5295 C XG-TW 93.46 XG-127 4.00 XG-301 2.20 XG-230 0.34	Formula	PANTONE 5305 C XG-TW 96.30 XG-127 2.23 XG-301 1.23 XG-230 0.24	Formula	PANTONE 5315 C XG-TW 98.61 XG-301 0.76 XG-127 0.63	Formula
PANTONE 532 C XG-TW 30.40 XG-165 26.60 XG-301 19.60 XG-064 14.70 XG-230 8.70	Formula	PANTONE 533 C XG-165 43.70 XG-TW 26.10 XG-064 13.90 XG-230 13.50 XG-301 2.80	Formula	PANTONE 534 C XG-TW 39.50 XG-165 37.00 XG-325 13.10 XG-230 6.60 XG-301 3.80	Formula	PANTONE 535 C XG-TW 90.96 XG-165 5.40 XG-064 2.01 XG-230 1.63	Formula
PANTONE 536 C XG-TW 94.02 XG-165 3.42 XG-064 1.47 XG-230 1.09	Formula	PANTONE 537 C XG-TW 96.14 XG-165 2.16 XG-064 1.02 XG-230 0.68	Formula	PANTONE 538 C XG-TW 97.32 XG-165 1.45 XG-064 0.77 XG-230 0.46	Formula	PANTONE 539 C XG-230 72.54 XG-TW 13.38 XG-301 8.69 XG-066 5.39	Formula
PANTONE 540 C XG-230 60.20 XG-TW 25.08 XG-127 7.93 XG-301 6.79	Formula	PANTONE 541 C XG-TW 33.72 XG-230 28.22 XG-MX 27.08 XG-127 6.69 XG-301 4.29	Formula	PANTONE 542 C XG-TW 88.61 XG-230 6.96 XG-127 3.16 XG-301 1.27	Formula	PANTONE 543 C XG-TW 96.04 XG-230 2.29 XG-127 1.12 XG-301 0.55	Formula

Plastijet XG

PANTONE 544 C XG-TW 98.27 XG-230 0.93 XG-127 0.59 XG-301 0.21	Formula	PANTONE 545 C XG-TW 99.06 XG-230 0.50 XG-127 0.32 XG-301 0.12	Formula	PANTONE 5395 C XG-230 45.89 XG-TW 24.78 XG-301 23.12 XG-127 6.21	Formula	PANTONE 5405 C XG-TW 74.06 XG-301 14.44 XG-230 8.09 XG-127 3.41	Formula
PANTONE 5415 C XG-TW 84.28 XG-301 8.75 XG-230 4.90 XG-127 2.07	Formula	PANTONE 5425 C XG-TW 92.54 XG-301 4.37 XG-230 2.06 XG-127 1.03	Formula	PANTONE 5435 C XG-TW 97.20 XG-301 1.64 XG-230 0.77 XG-127 0.39	Formula	PANTONE 5445 C XG-TW 98.82 XG-301 0.67 XG-230 0.31 XG-127 0.20	Formula
PANTONE 5455 C XG-TW 99.35 XG-301 0.37 XG-230 0.17 XG-127 0.11	Formula	PANTONE 546 C XG-230 39.23 XG-TW 33.28 XG-301 23.40 XG-066 4.09	Formula	PANTONE 547 C XG-230 47.60 XG-TW 30.52 XG-301 16.72 XG-066 5.16	Formula	PANTONE 548 C XG-230 44.92 XG-TW 41.73 XG-301 10.20 XG-066 3.15	Formula
PANTONE 549 C XG-TW 89.74 XG-230 6.41 XG-301 3.85	Formula	PANTONE 550 C XG-TW 95.09 XG-230 3.06 XG-301 1.85	Formula	PANTONE 551 C XG-TW 97.56 XG-230 1.33 XG-301 1.11	Formula	PANTONE 552 C XG-TW 98.94 XG-230 0.58 XG-301 0.48	Formula

Plastijet XG

PANTONE 5463 C XG-TW 39.61 XG-230 26.82 XG-301 17.29 XG-064 16.28	Formula	PANTONE 5473 C XG-TW 67.12 XG-230 14.55 XG-064 10.65 XG-301 7.68	Formula	PANTONE 5483 C XG-TW 85.49 XG-230 5.56 XG-301 4.88 XG-064 4.07	Formula	PANTONE 5493 C XG-TW 93.64 XG-230 2.68 XG-301 2.34 XG-064 1.34	Formula
PANTONE 5503 C XG-TW 96.98 XG-301 1.15 XG-230 1.10 XG-064 0.77	Formula	PANTONE 5513 C XG-TW 98.63 XG-301 0.50 XG-230 0.50 XG-064 0.37	Formula	PANTONE 5523 C XG-TW 99.21 XG-301 0.27 XG-230 0.27 XG-064 0.25	Formula	PANTONE 5467 C XG-064 31.88 XG-230 25.37 XG-301 18.54 XG-TW 14.59 XG-MX 9.62	Formula
PANTONE 5477 C XG-TW 42.50 XG-064 32.45 XG-127 17.75 XG-230 7.14 XG-301 0.16	Formula	PANTONE 5487 C XG-TW 71.09 XG-064 16.57 XG-127 9.06 XG-230 3.02 XG-301 0.26	Formula	PANTONE 5497 C XG-TW 88.35 XG-064 6.52 XG-127 3.85 XG-230 1.28	Formula	PANTONE 5507 C XG-TW 93.40 XG-064 3.63 XG-127 2.31 XG-230 0.66	Formula
PANTONE 5517 C XG-TW 96.02 XG-064 2.20 XG-127 1.34 XG-230 0.44	Formula	PANTONE 5527 C XG-TW 97.38 XG-064 1.45 XG-127 0.87 XG-230 0.30	Formula	PANTONE 553 C XG-064 43.26 XG-TW 18.79 XG-301 14.64 XG-230 13.73 XG-MX 9.58	Formula	PANTONE 554 C XG-TW 38.39 XG-064 32.76 XG-230 10.47 XG-MX 9.44 XG-301 8.94	Formula

Plastijet XG

PANTONE 555 C XG-TW 51.38 XG-064 30.20 XG-230 12.65 XG-301 5.77	Formula	PANTONE 556 C XG-TW 86.19 XG-064 8.94 XG-127 2.64 XG-230 2.23	Formula	PANTONE 557 C XG-TW 93.49 XG-064 4.16 XG-127 1.38 XG-230 0.97	Formula	PANTONE 558 C XG-TW 96.07 XG-064 2.43 XG-127 0.89 XG-230 0.61	Formula
PANTONE 559 C XG-TW 97.29 XG-064 1.72 XG-127 0.55 XG-230 0.44	Formula	PANTONE 5535 C XG-064 39.71 XG-301 22.44 XG-325 22.42 XG-TW 15.43	Formula	PANTONE 5545 C XG-TW 66.74 XG-064 13.10 XG-301 10.90 XG-325 9.26	Formula	PANTONE 5555 C XG-TW 87.36 XG-301 5.40 XG-064 4.61 XG-325 2.63	Formula
PANTONE 5565 C XG-TW 92.93 XG-301 3.02 XG-064 2.16 XG-325 1.89	Formula	PANTONE 5575 C XG-TW 96.25 XG-301 1.72 XG-064 1.14 XG-325 0.89	Formula	PANTONE 5585 C XG-TW 97.92 XG-301 0.89 XG-064 0.76 XG-325 0.43	Formula	PANTONE 5595 C XG-TW 98.28 XG-301 0.72 XG-064 0.71 XG-325 0.29	Formula
PANTONE 560 C XG-TW 38.05 XG-325 27.67 XG-066 17.80 XG-301 16.48	Formula	PANTONE 561 C XG-TW 58.86 XG-325 27.27 XG-301 8.35 XG-064 5.52	Formula	PANTONE 562 C XG-TW 76.27 XG-325 16.39 XG-301 5.00 XG-064 2.34	Formula	PANTONE 563 C XG-TW 93.17 XG-325 4.35 XG-301 1.86 XG-064 0.62	Formula

Plastijet XG

PANTONE 564 C XG-TW 96.38 XG-325 2.31 XG-301 0.98 XG-064 0.33	Formula	PANTONE 565 C XG-TW 97.84 XG-325 1.38 XG-301 0.58 XG-064 0.20	Formula	PANTONE 566 C XG-TW 98.89 XG-325 0.71 XG-301 0.30 XG-064 0.10	Formula	PANTONE 5605 C XG-064 45.00 XG-301 20.64 XG-230 12.97 XG-TW 11.76 XG-MX 9.63	Formula
PANTONE 5615 C XG-TW 65.78 XG-064 18.42 XG-301 12.18 XG-230 3.62	Formula	PANTONE 5625 C XG-TW 81.84 XG-064 9.06 XG-301 7.26 XG-230 1.84	Formula	PANTONE 5635 C XG-TW 93.20 XG-064 3.00 XG-301 3.00 XG-230 0.80	Formula	PANTONE 5645 C XG-TW 97.01 XG-301 1.49 XG-064 1.25 XG-230 0.25	Formula
PANTONE 5655 C XG-TW 97.77 XG-301 1.05 XG-064 1.00 XG-230 0.18	Formula	PANTONE 5665 C XG-TW 98.48 XG-064 0.69 XG-301 0.68 XG-230 0.15	Formula	PANTONE 567 C XG-TW 48.05 XG-325 21.19 XG-301 13.16 XG-MX 9.36 XG-066 8.24	Formula	PANTONE 568 C XG-TW 63.00 XG-325 29.70 XG-301 3.60 XG-114 2.70 XG-066 1.00	Formula
PANTONE 569 C XG-TW 69.40 XG-325 26.40 XG-301 2.70 XG-114 1.30 XG-066 0.20	Formula	PANTONE 570 C XG-TW 95.11 XG-325 4.09 XG-114 0.41 XG-127 0.39	Formula	PANTONE 571 C XG-TW 97.56 XG-325 2.02 XG-114 0.24 XG-127 0.18	Formula	PANTONE 572 C XG-TW 98.49 XG-325 1.27 XG-114 0.14 XG-127 0.10	Formula

Plastijet XG

PANTONE 573 C XG-TW 99.07 XG-325 0.80 XG-114 0.13	Formula	PANTONE 574 C XG-064 61.00 XG-TW 14.02 XG-301 13.07 XG-MX 9.60 XG-230 2.31	Formula	PANTONE 575 C XG-064 65.95 XG-TW 12.65 XG-MX 9.60 XG-301 7.24 XG-230 4.56	Formula	PANTONE 576 C XG-064 56.49 XG-TW 35.97 XG-230 3.80 XG-301 3.74	Formula
PANTONE 577 C XG-TW 89.33 XG-064 9.11 XG-127 0.94 XG-230 0.62	Formula	PANTONE 578 C XG-TW 91.16 XG-064 7.47 XG-127 0.84 XG-230 0.53	Formula	PANTONE 579 C XG-TW 93.89 XG-064 5.07 XG-127 0.66 XG-230 0.38	Formula	PANTONE 580 C XG-TW 96.24 XG-064 3.14 XG-127 0.39 XG-230 0.23	Formula
PANTONE 5743 C XG-066 51.27 XG-325 21.36 XG-121 14.96 XG-TW 8.56 XG-301 3.85	Formula	PANTONE 5753 C XG-TW 57.88 XG-066 27.09 XG-127 8.78 XG-230 4.30 XG-301 1.95	Formula	PANTONE 5763 C XG-TW 73.18 XG-066 17.20 XG-127 6.75 XG-230 2.87	Formula	PANTONE 5773 C XG-TW 89.10 XG-066 6.26 XG-127 3.38 XG-230 1.26	Formula
PANTONE 5783 C XG-TW 94.06 XG-066 3.15 XG-127 2.06 XG-230 0.73	Formula	PANTONE 5793 C XG-TW 96.43 XG-066 1.84 XG-127 1.29 XG-230 0.44	Formula	PANTONE 5803 C XG-TW 98.14 XG-066 0.98 XG-127 0.67 XG-230 0.21	Formula	PANTONE 5747 C XG-064 65.86 XG-MX 9.71 XG-301 8.29 XG-114 8.26 XG-230 7.88	Formula

Plastijet XG

PANTONE 5757 C XG-TW 43.08 XG-066 38.38 XG-MX 9.49 XG-301 6.41 XG-230 2.64	Formula	PANTONE 5767 C XG-TW 74.10 XG-066 12.14 XG-MX 9.23 XG-301 3.66 XG-230 0.87	Formula	PANTONE 5777 C XG-TW 90.10 XG-066 6.90 XG-230 1.60 XG-164 1.40	Formula	PANTONE 5787 C XG-TW 96.42 XG-066 2.33 XG-230 0.66 XG-164 0.59	Formula
PANTONE 5797 C XG-TW 97.66 XG-066 1.49 XG-164 0.43 XG-230 0.42	Formula	PANTONE 5807 C XG-TW 98.54 XG-066 0.94 XG-230 0.27 XG-164 0.25	Formula	PANTONE 581 C XG-064 88.09 XG-127 5.88 XG-301 5.22 XG-230 0.81	Formula	PANTONE 582 C XG-064 95.07 XG-127 2.76 XG-230 1.14 XG-301 0.70 XG-TW 0.33	Formula
PANTONE 583 C XG-064 92.04 XG-TW 6.30 XG-230 0.96 XG-127 0.70	Formula	PANTONE 584 C XG-TW 69.50 XG-064 29.60 XG-127 0.50 XG-230 0.40	Formula	PANTONE 585 C XG-TW 83.37 XG-064 16.17 XG-127 0.31 XG-230 0.15	Formula	PANTONE 586 C XG-TW 89.23 XG-064 10.23 XG-127 0.39 XG-230 0.15	Formula
PANTONE 587 C XG-TW 94.77 XG-064 5.02 XG-127 0.21	Formula	PANTONE 5815 C XG-064 81.43 XG-301 15.81 XG-121 2.76	Formula	PANTONE 5825 C XG-TW 47.04 XG-064 45.18 XG-301 7.24 XG-114 0.54	Formula	PANTONE 5835 C XG-TW 70.10 XG-064 25.36 XG-301 4.22 XG-114 0.32	Formula

Plastijet XG

PANTONE 5845 C XG-TW 79.10 XG-064 16.39 XG-301 3.95 XG-114 0.56	Formula	PANTONE 5855 C XG-TW 91.16 XG-064 6.92 XG-301 1.68 XG-114 0.24	Formula	PANTONE 5865 C XG-TW 94.11 XG-064 4.61 XG-301 1.12 XG-114 0.16	Formula	PANTONE 5875 C XG-TW 97.17 XG-064 2.22 XG-301 0.51 XG-114 0.10	Formula
PANTONE 600 C XG-TW 96.67 XG-064 3.22 XG-114 0.11	Formula	PANTONE 601 C XG-TW 93.27 XG-064 6.59 XG-301 0.14	Formula	PANTONE 602 C XG-TW 83.56 XG-064 16.34 XG-301 0.10	Formula	PANTONE 603 C XG-TW 69.83 XG-064 29.92 XG-301 0.15 XG-114 0.10	Formula
PANTONE 604 C XG-064 63.50 XG-TW 35.70 XG-301 0.62 XG-114 0.18	Formula	PANTONE 605 C XG-064 70.56 XG-TW 28.80 XG-301 0.64	Formula	PANTONE 606 C XG-064 71.74 XG-TW 27.42 XG-301 0.84	Formula	PANTONE 607 C XG-TW 97.37 XG-064 2.53 XG-114 0.10	Formula
PANTONE 608 C XG-TW 96.07 XG-064 3.73 XG-114 0.10 XG-301 0.10	Formula	PANTONE 609 C XG-TW 93.43 XG-064 6.32 XG-301 0.15 XG-114 0.10	Formula	PANTONE 610 C XG-TW 82.93 XG-064 16.59 XG-301 0.34 XG-114 0.14	Formula	PANTONE 611 C XG-TW 73.43 XG-064 25.89 XG-301 0.68	Formula

Plastijet XG

PANTONE 612 C XG-TW 53.08 XG-064 45.55 XG-301 1.37	Formula	PANTONE 613 C XG-064 62.33 XG-TW 35.04 XG-301 2.08 XG-114 0.55	Formula	PANTONE 614 C XG-TW 97.71 XG-064 1.86 XG-301 0.30 XG-121 0.13	Formula	PANTONE 615 C XG-TW 96.53 XG-064 2.97 XG-301 0.38 XG-121 0.12	Formula
PANTONE 616 C XG-TW 94.58 XG-064 4.66 XG-301 0.63 XG-121 0.13	Formula	PANTONE 617 C XG-TW 85.86 XG-064 12.12 XG-301 1.67 XG-121 0.35	Formula	PANTONE 618 C XG-TW 71.09 XG-064 26.34 XG-301 2.12 XG-121 0.45	Formula	PANTONE 619 C XG-TW 41.24 XG-064 41.24 XG-066 13.40 XG-301 4.12	Formula
PANTONE 620 C XG-TW 39.42 XG-064 39.42 XG-066 16.03 XG-301 5.13	Formula	PANTONE 621 C XG-TW 98.98 XG-064 0.40 XG-301 0.36 XG-325 0.26	Formula	PANTONE 622 C XG-TW 97.79 XG-301 0.87 XG-064 0.77 XG-325 0.57	Formula	PANTONE 623 C XG-TW 94.86 XG-301 1.85 XG-064 1.69 XG-325 1.60	Formula
PANTONE 624 C XG-TW 88.38 XG-064 4.25 XG-301 3.80 XG-325 3.57	Formula	PANTONE 625 C XG-TW 77.98 XG-064 8.42 XG-325 7.50 XG-301 6.10	Formula	PANTONE 626 C XG-TW 43.81 XG-064 24.80 XG-325 16.68 XG-301 14.71	Formula	PANTONE 627 C XG-301 33.17 XG-064 31.06 XG-325 29.64 XG-TW 6.13	Formula

Plastijet XG

PANTONE 628 C XG-TW 99.23 XG-325 0.34 XG-230 0.31 XG-301 0.12	Formula	PANTONE 629 C XG-TW 89.63 XG-MX 9.10 XG-230 0.72 XG-325 0.38 XG-301 0.17	Formula	PANTONE 630 C XG-TW 79.19 XG-MX 18.37 XG-230 1.53 XG-325 0.51 XG-301 0.40	Formula	PANTONE 631 C XG-TW 75.65 XG-MX 18.45 XG-230 4.04 XG-325 1.30 XG-301 0.56	Formula
PANTONE 632 C XG-TW 77.61 XG-MX 9.18 XG-230 8.29 XG-325 3.61 XG-301 1.31	Formula	PANTONE 633 C XG-TW 50.53 XG-MX 23.52 XG-230 18.83 XG-325 5.09 XG-301 2.03	Formula	PANTONE 634 C XG-230 38.61 XG-TW 32.32 XG-MX 18.82 XG-325 9.26 XG-301 0.99	Formula	PANTONE 635 C XG-TW 99.08 XG-230 0.72 XG-064 0.20	Formula
PANTONE 636 C XG-TW 98.37 XG-230 1.52 XG-064 0.11	Formula	PANTONE 637 C XG-TW 96.42 XG-230 3.33 XG-064 0.25	Formula	PANTONE 638 C XG-TW 72.10 XG-MX 20.68 XG-230 6.47 XG-064 0.75	Formula	PANTONE 639 C XG-TW 82.01 XG-230 15.03 XG-325 2.96	Formula
PANTONE 640 C XG-TW 53.60 XG-230 24.51 XG-MX 18.75 XG-325 3.14	Formula	PANTONE 641 C XG-TW 45.20 XG-230 33.42 XG-MX 18.87 XG-325 2.51	Formula	PANTONE 642 C XG-TW 98.91 XG-301 0.42 XG-230 0.35 XG-127 0.32	Formula	PANTONE 643 C XG-TW 98.33 XG-230 0.60 XG-301 0.56 XG-127 0.51	Formula

Plastijet XG

PANTONE 644 C XG-TW 96.28 XG-230 1.31 XG-127 1.28 XG-301 1.13	Formula	PANTONE 645 C XG-TW 92.49 XG-230 2.77 XG-127 2.47 XG-301 2.27	Formula	PANTONE 646 C XG-TW 84.66 XG-230 6.13 XG-127 5.11 XG-301 4.10	Formula	PANTONE 647 C XG-TW 53.91 XG-MX 18.81 XG-230 13.16 XG-127 8.02 XG-301 6.10	Formula
PANTONE 648 C XG-230 68.47 XG-TW 21.52 XG-301 7.75 XG-127 2.26	Formula	PANTONE 649 C XG-TW 98.93 XG-127 0.61 XG-230 0.25 XG-066 0.21	Formula	PANTONE 650 C XG-TW 97.60 XG-127 1.40 XG-230 0.60 XG-066 0.40	Formula	PANTONE 651 C XG-TW 94.68 XG-127 3.28 XG-230 1.29 XG-066 0.75	Formula
PANTONE 652 C XG-TW 86.90 XG-127 7.88 XG-230 3.67 XG-066 1.55	Formula	PANTONE 653 C XG-TW 59.65 XG-127 23.25 XG-230 13.03 XG-066 4.07	Formula	PANTONE 654 C XG-230 87.60 XG-301 12.40	Formula	PANTONE 655 C XG-230 76.88 XG-301 13.92 XG-127 9.20	Formula
PANTONE 656 C XG-TW 98.71 XG-127 0.71 XG-230 0.30 XG-064 0.28	Formula	PANTONE 657 C XG-TW 97.65 XG-127 1.33 XG-230 0.65 XG-064 0.37	Formula	PANTONE 658 C XG-TW 95.07 XG-127 2.88 XG-230 1.47 XG-064 0.58	Formula	PANTONE 659 C XG-TW 88.85 XG-127 6.17 XG-230 3.95 XG-064 1.03	Formula

Plastijet XG

PANTONE 660 C XG-TW 63.15 XG-230 14.79 XG-127 11.54 XG-MX 9.31 XG-064 1.21	Formula	PANTONE 661 C XG-230 34.60 XG-MX 25.10 XG-127 22.60 XG-TW 16.80 XG-301 0.90	Formula	PANTONE 662 C XG-230 64.10 XG-127 25.64 XG-TW 10.26	Formula	PANTONE 663 C XG-TW 98.95 XG-127 0.59 XG-301 0.36 XG-066 0.10	Formula
PANTONE 664 C XG-TW 98.18 XG-127 1.25 XG-301 0.38 XG-066 0.19	Formula	PANTONE 665 C XG-TW 96.53 XG-127 2.42 XG-301 0.60 XG-066 0.45	Formula	PANTONE 666 C XG-TW 92.75 XG-127 5.24 XG-301 1.17 XG-066 0.74 XG-114 0.10	Formula	PANTONE 667 C XG-TW 78.75 XG-127 16.05 XG-301 3.15 XG-066 1.65 XG-114 0.40	Formula
PANTONE 668 C XG-TW 69.00 XG-127 27.06 XG-301 2.40 XG-114 0.92 XG-066 0.62	Formula	PANTONE 669 C XG-127 48.37 XG-TW 34.51 XG-MX 13.66 XG-066 3.46	Formula	PANTONE 670 C XG-TW 98.59 XG-165 1.31 XG-114 0.10	Formula	PANTONE 671 C XG-TW 97.50 XG-165 2.20 XG-114 0.20 XG-230 0.10	Formula
PANTONE 672 C XG-TW 93.58 XG-165 5.71 XG-114 0.51 XG-230 0.20	Formula	PANTONE 673 C XG-TW 87.01 XG-165 11.89 XG-114 0.78 XG-230 0.32	Formula	PANTONE 674 C XG-TW 75.39 XG-165 19.75 XG-121 4.03 XG-301 0.83	Formula	PANTONE 675 C XG-165 53.06 XG-TW 40.00 XG-121 5.57 XG-301 1.37	Formula

Plastijet XG

PANTONE 676 C XG-165 72.83 XG-TW 17.29 XG-121 8.36 XG-301 1.52	Formula	PANTONE 677 C XG-TW 99.28 XG-164 0.39 XG-064 0.19 XG-301 0.14	Formula	PANTONE 678 C XG-TW 98.94 XG-164 0.60 XG-301 0.25 XG-064 0.21	Formula	PANTONE 679 C XG-TW 98.56 XG-164 0.85 XG-301 0.42 XG-064 0.17	Formula
PANTONE 680 C XG-TW 96.29 XG-164 2.29 XG-301 0.95 XG-064 0.47	Formula	PANTONE 681 C XG-TW 89.68 XG-164 7.13 XG-301 2.17 XG-064 1.02	Formula	PANTONE 682 C XG-TW 79.19 XG-164 16.54 XG-301 2.99 XG-064 1.28	Formula	PANTONE 683 C XG-TW 51.93 XG-164 41.92 XG-301 5.16 XG-064 0.99	Formula
PANTONE 684 C XG-TW 98.41 XG-121 1.28 XG-301 0.31	Formula	PANTONE 685 C XG-TW 97.69 XG-121 1.68 XG-301 0.45 XG-165 0.18	Formula	PANTONE 686 C XG-TW 95.85 XG-121 2.55 XG-165 0.83 XG-301 0.77	Formula	PANTONE 687 C XG-TW 88.02 XG-121 5.82 XG-165 4.48 XG-301 1.68	Formula
PANTONE 688 C XG-TW 77.49 XG-165 9.87 XG-121 9.73 XG-301 2.91	Formula	PANTONE 689 C XG-TW 52.11 XG-165 28.98 XG-121 14.22 XG-301 4.69	Formula	PANTONE 690 C XG-165 44.13 XG-TW 29.14 XG-121 18.90 XG-301 7.83	Formula	PANTONE 691 C XG-TW 98.80 XG-165 0.70 XG-114 0.30 XG-301 0.20	Formula

Plastijet XG

PANTONE 692 C XG-TW 97.10 XG-165 1.80 XG-114 0.70 XG-301 0.40	Formula	PANTONE 693 C XG-TW 94.50 XG-165 3.70 XG-114 1.00 XG-301 0.80	Formula	PANTONE 694 C XG-TW 86.96 XG-165 8.70 XG-114 2.17 XG-301 2.17	Formula	PANTONE 695 C XG-TW 71.30 XG-165 20.80 XG-114 5.30 XG-301 2.60	Formula
PANTONE 696 C XG-165 51.40 XG-TW 32.70 XG-114 10.50 XG-301 5.40	Formula	PANTONE 697 C XG-165 68.20 XG-TW 14.60 XG-114 10.00 XG-301 7.20	Formula	PANTONE 698 C XG-TW 98.70 XG-165 0.50 XG-121 0.50 XG-114 0.30	Formula	PANTONE 699 C XG-TW 97.80 XG-165 0.90 XG-121 0.90 XG-114 0.40	Formula
PANTONE 700 C XG-TW 94.00 XG-121 2.50 XG-165 2.40 XG-114 1.00 XG-301 0.10	Formula	PANTONE 701 C XG-TW 81.30 XG-165 11.38 XG-121 4.07 XG-114 2.44 XG-301 0.81	Formula	PANTONE 702 C XG-TW 75.35 XG-121 21.64 XG-301 3.01	Formula	PANTONE 703 C XG-165 40.60 XG-121 35.50 XG-TW 17.80 XG-114 3.50 XG-301 2.60	Formula
PANTONE 704 C XG-165 49.40 XG-121 43.10 XG-114 4.20 XG-301 3.30	Formula	PANTONE 705 C XG-TW 99.40 XG-121 0.50 XG-114 0.10	Formula	PANTONE 706 C XG-TW 98.16 XG-121 1.67 XG-114 0.17	Formula	PANTONE 707 C XG-TW 95.78 XG-121 3.91 XG-114 0.31	Formula

Plastijet XG

PANTONE 708 C XG-TW 91.37 XG-121 8.12 XG-114 0.51	Formula	PANTONE 709 C XG-TW 76.90 XG-121 22.20 XG-114 0.60 XG-301 0.30	Formula	PANTONE 710 C XG-121 51.87 XG-TW 47.83 XG-301 0.30	Formula	PANTONE 711 C XG-121 67.44 XG-TW 31.86 XG-301 0.70	Formula
PANTONE 712 C XG-TW 98.92 XG-114 0.87 XG-066 0.21	Formula	PANTONE 713 C XG-TW 98.29 XG-114 1.41 XG-066 0.30	Formula	PANTONE 714 C XG-TW 95.85 XG-114 2.98 XG-066 1.04 XG-301 0.13	Formula	PANTONE 715 C XG-TW 88.93 XG-114 6.31 XG-066 4.46 XG-301 0.30	Formula
PANTONE 716 C XG-TW 74.74 XG-114 13.45 XG-066 11.15 XG-301 0.66	Formula	PANTONE 717 C XG-066 57.76 XG-114 31.51 XG-TW 9.61 XG-301 1.12	Formula	PANTONE 718 C XG-066 64.47 XG-114 29.64 XG-TW 4.41 XG-301 1.48	Formula	PANTONE 719 C XG-TW 98.46 XG-114 0.77 XG-064 0.52 XG-301 0.25	Formula
PANTONE 720 C XG-TW 97.70 XG-114 1.15 XG-064 0.72 XG-301 0.43	Formula	PANTONE 721 C XG-TW 95.92 XG-114 1.89 XG-064 1.52 XG-301 0.67	Formula	PANTONE 722 C XG-TW 83.48 XG-064 8.66 XG-114 6.04 XG-301 1.82	Formula	PANTONE 723 C XG-TW 63.92 XG-064 22.47 XG-114 10.84 XG-301 2.77	Formula

Plastijet XG

PANTONE 724 C XG-064 57.15 XG-114 29.21 XG-TW 7.85 XG-301 5.79	Formula	PANTONE 725 C XG-114 73.85 XG-TW 18.20 XG-301 7.95	Formula	PANTONE 726 C XG-TW 98.78 XG-114 0.60 XG-301 0.40 XG-066 0.22	Formula	PANTONE 727 C XG-TW 97.90 XG-114 0.98 XG-301 0.69 XG-066 0.43	Formula
PANTONE 728 C XG-TW 96.05 XG-114 1.83 XG-301 1.18 XG-066 0.94	Formula	PANTONE 729 C XG-TW 91.00 XG-114 4.06 XG-066 2.80 XG-301 2.14	Formula	PANTONE 730 C XG-TW 81.06 XG-066 7.81 XG-114 7.75 XG-301 3.38	Formula	PANTONE 731 C XG-114 52.35 XG-066 30.39 XG-301 10.17 XG-TW 7.09	Formula
PANTONE 732 C XG-114 84.84 XG-301 13.68 XG-TW 1.48	Formula	PANTONE 7401 C XG-TW 95.89 XG-064 3.44 XG-121 0.67	Formula	PANTONE 7402 C XG-TW 91.14 XG-064 7.93 XG-121 0.93	Formula	PANTONE 7403 C XG-TW 77.54 XG-064 19.61 XG-121 1.47 XG-SB 1.38	Formula
PANTONE 7404 C XG-064 74.26 XG-TW 25.16 XG-121 0.58	Formula	PANTONE 7405 C XG-064 75.69 XG-066 22.01 XG-SB 2.30	Formula	PANTONE 7406 C XG-066 54.54 XG-064 42.40 XG-SB 3.06	Formula	PANTONE 7407 C XG-TW 86.46 XG-066 5.72 XG-SB 5.34 XG-121 2.48	Formula

Plastijet XG

PANTONE 7408 C XG-066 57.96 XG-064 40.67 XG-121 1.16 XG-325 0.21	Formula	PANTONE 7409 C XG-064 78.18 XG-066 17.74 XG-121 2.47 XG-SB 1.61	Formula	PANTONE 7410 C XG-TW 86.78 XG-114 8.94 XG-066 3.15 XG-SB 1.13	Formula	PANTONE 7411 C XG-TW 64.19 XG-066 22.12 XG-114 8.02 XG-SB 5.67	Formula
PANTONE 7412 C XG-066 78.55 XG-114 12.70 XG-SB 8.75	Formula	PANTONE 7413 C XG-064 68.22 XG-TW 24.82 XG-164 4.66 XG-SB 2.30	Formula	PANTONE 7414 C XG-TW 47.52 XG-114 30.02 XG-066 20.93 XG-230 1.53	Formula	PANTONE 7415 C XG-TW 94.32 XG-064 4.20 XG-164 1.41 XG-325 0.07	Formula
PANTONE 7416 C XG-TW 56.13 XG-064 35.00 XG-164 8.87	Formula	PANTONE 7417 C XG-064 38.56 XG-TW 25.63 XG-MX 25.00 XG-164 10.81	Formula	PANTONE 7418 C XG-121 50.22 XG-TW 44.41 XG-SB 5.37	Formula	PANTONE 7419 C XG-121 51.27 XG-TW 47.25 XG-230 1.48	Formula
PANTONE 7420 C XG-121 46.80 XG-165 31.88 XG-TW 19.90 XG-230 1.42	Formula	PANTONE 7421 C XG-121 66.43 XG-165 29.40 XG-230 4.17	Formula	PANTONE 7422 C XG-TW 98.67 XG-121 1.33	Formula	PANTONE 7423 C XG-TW 74.83 XG-121 12.95 XG-165 12.15 XG-230 0.07	Formula

Plastijet XG

PANTONE 7424 C XG-TW 76.45 XG-164 23.55	Formula	PANTONE 7425 C XG-165 39.91 XG-TW 23.16 XG-121 21.39 XG-MX 15.00 XG-325 0.54	Formula	PANTONE 7426 C XG-121 37.44 XG-165 31.74 XG-TW 15.10 XG-MX 14.99 XG-230 0.73	Formula	PANTONE 7427 C XG-165 70.06 XG-066 14.90 XG-TW 13.70 XG-325 1.34	Formula
PANTONE 7428 C XG-165 50.75 XG-SB 25.98 XG-TW 18.20 XG-066 5.07	Formula	PANTONE 7429 C XG-TW 97.89 XG-SB 1.26 XG-164 0.79 XG-066 0.06	Formula	PANTONE 7430 C XG-TW 96.31 XG-164 1.39 XG-064 1.32 XG-127 0.98	Formula	PANTONE 7431 C XG-TW 94.00 XG-164 3.71 XG-064 1.91 XG-230 0.38	Formula
PANTONE 7432 C XG-TW 82.31 XG-164 9.34 XG-SB 6.10 XG-064 2.25	Formula	PANTONE 7433 C XG-TW 70.06 XG-164 19.11 XG-SB 7.01 XG-064 3.82	Formula	PANTONE 7434 C XG-TW 58.65 XG-164 25.74 XG-SB 10.18 XG-064 5.43	Formula	PANTONE 7435 C XG-TW 49.47 XG-164 33.39 XG-SB 14.13 XG-064 3.01	Formula
PANTONE 7436 C XG-TW 98.34 XG-165 1.18 XG-127 0.48	Formula	PANTONE 7437 C XG-TW 95.37 XG-165 2.17 XG-127 1.25 XG-SB 1.21	Formula	PANTONE 7438 C XG-TW 90.01 XG-165 7.65 XG-127 2.34	Formula	PANTONE 7439 C XG-TW 95.81 XG-164 3.17 XG-230 1.02	Formula

Plastijet XG

PANTONE 7440 C XG-TW 75.45 XG-MX 15.00 XG-SB 4.36 XG-127 3.16 XG-164 2.03	Formula	PANTONE 7441 C XG-TW 62.64 XG-MX 20.00 XG-165 9.22 XG-127 8.14	Formula	PANTONE 7442 C XG-TW 58.96 XG-127 21.04 XG-MX 20.00	Formula	PANTONE 7443 C XG-TW 98.85 XG-127 1.02 XG-230 0.13	Formula
PANTONE 7444 C XG-TW 97.31 XG-127 2.30 XG-230 0.39	Formula	PANTONE 7445 C XG-TW 95.00 XG-127 3.43 XG-SB 1.12 XG-325 0.45	Formula	PANTONE 7446 C XG-TW 54.24 XG-MX 40.00 XG-127 5.10 XG-230 0.66	Formula	PANTONE 7447 C XG-MX 40.00 XG-TW 32.64 XG-SB 15.95 XG-127 11.41	Formula
PANTONE 7448 C XG-MX 40.00 XG-SB 34.74 XG-TW 15.98 XG-127 7.13 XG-121 2.15	Formula	PANTONE 7449 C XG-SB 51.58 XG-MX 39.30 XG-121 7.62 XG-127 1.50	Formula	PANTONE 7450 C XG-TW 98.29 XG-127 1.35 XG-230 0.36	Formula	PANTONE 7451 C XG-TW 95.39 XG-127 3.04 XG-230 1.57	Formula
PANTONE 7452 C XG-TW 92.41 XG-127 5.80 XG-230 1.79	Formula	PANTONE 7453 C XG-TW 94.87 XG-127 3.13 XG-230 2.00	Formula	PANTONE 7454 C XG-TW 54.47 XG-MX 40.00 XG-230 3.09 XG-164 1.80 XG-064 0.64	Formula	PANTONE 7455 C XG-TW 46.97 XG-MX 40.00 XG-127 7.23 XG-230 4.72 XG-164 1.08	Formula

Plastijet XG

PANTONE 7456 C XG-TW 51.87 XG-MX 40.00 XG-127 4.36 XG-230 2.53 XG-164 1.24	Formula	PANTONE 7457 C XG-TW 99.10 XG-230 0.47 XG-127 0.43	Formula	PANTONE 7458 C XG-TW 75.56 XG-MX 20.50 XG-230 2.46 XG-121 1.48	Formula	PANTONE 7459 C XG-TW 56.26 XG-MX 37.92 XG-230 4.51 XG-164 0.81 XG-114 0.50	Formula
PANTONE 7460 C XG-TW 43.76 XG-MX 40.00 XG-230 14.97 XG-325 1.27	Formula	PANTONE 7461 C XG-TW 82.47 XG-230 11.20 XG-165 6.05 XG-066 0.28	Formula	PANTONE 7462 C XG-TW 70.91 XG-230 17.62 XG-121 11.47	Formula	PANTONE 7463 C XG-MX 40.00 XG-SB 38.41 XG-165 16.00 XG-230 5.59	Formula
PANTONE 7464 C XG-TW 98.02 XG-230 1.20 XG-064 0.61 XG-164 0.17	Formula	PANTONE 7465 C XG-TW 93.62 XG-230 3.47 XG-064 2.60 XG-066 0.31	Formula	PANTONE 7466 C XG-TW 51.26 XG-MX 40.00 XG-230 4.84 XG-325 3.90	Formula	PANTONE 7467 C XG-TW 47.80 XG-MX 40.00 XG-230 6.55 XG-325 5.65	Formula
PANTONE 7468 C XG-TW 76.68 XG-230 11.48 XG-SB 9.88 XG-121 1.96	Formula	PANTONE 7469 C XG-TW 63.85 XG-SB 17.54 XG-230 15.78 XG-165 2.83	Formula	PANTONE 7470 C XG-MX 40.00 XG-TW 26.39 XG-165 15.57 XG-230 9.68 XG-064 8.36	Formula	PANTONE 7471 C XG-TW 97.58 XG-325 1.53 XG-230 0.89	Formula

Plastijet XG

PANTONE 7472 C XG-TW 94.96 XG-230 3.96 XG-066 0.71 XG-114 0.37	Formula	PANTONE 7473 C XG-TW 85.33 XG-230 7.98 XG-066 3.38 XG-SB 3.31	Formula	PANTONE 7474 C XG-TW 53.40 XG-MX 20.00 XG-230 17.09 XG-325 7.46 XG-114 2.05	Formula	PANTONE 7475 C XG-TW 51.11 XG-SB 21.47 XG-MX 20.00 XG-230 4.89 XG-064 2.53	Formula
PANTONE 7476 C XG-TW 37.96 XG-230 30.76 XG-MX 20.00 XG-114 7.74 XG-064 3.54	Formula	PANTONE 7477 C XG-SB 52.77 XG-TW 34.26 XG-230 12.97	Formula	PANTONE 7478 C XG-TW 97.08 XG-325 1.47 XG-064 1.25 XG-230 0.20	Formula	PANTONE 7479 C XG-TW 81.24 XG-064 11.97 XG-325 6.57 XG-230 0.22	Formula
PANTONE 7480 C XG-TW 52.44 XG-MX 20.00 XG-064 14.20 XG-325 13.36	Formula	PANTONE 7481 C XG-TW 35.41 XG-064 29.56 XG-MX 20.00 XG-325 15.03	Formula	PANTONE 7482 C XG-TW 37.15 XG-064 30.99 XG-230 6.09 XG-325 25.77	Formula	PANTONE 7483 C XG-SB 38.67 XG-TW 23.58 XG-064 17.89 XG-325 14.84 XG-066 5.02	Formula
PANTONE 7484 C XG-325 47.24 XG-TW 36.39 XG-121 7.93 XG-066 4.78 XG-114 3.66	Formula	PANTONE 7485 C XG-TW 98.20 XG-064 0.87 XG-SB 0.71 XG-230 0.22	Formula	PANTONE 7486 C XG-TW 94.51 XG-064 4.96 XG-230 0.53	Formula	PANTONE 7487 C XG-TW 80.54 XG-064 17.27 XG-325 1.92 XG-230 0.27	Formula

Plastijet XG

PANTONE 7488 C XG-TW 59.03 XG-064 36.80 XG-325 4.17	Formula	PANTONE 7489 C XG-TW 57.67 XG-064 38.45 XG-230 3.06 XG-164 0.82	Formula	PANTONE 7490 C XG-064 43.05 XG-TW 31.94 XG-MX 20.00 XG-230 3.39 XG-164 1.62	Formula	PANTONE 7491 C XG-064 46.23 XG-TW 32.72 XG-SB 19.80 XG-230 1.25	Formula
PANTONE 7492 C XG-TW 88.97 XG-064 9.01 XG-165 1.33 XG-230 0.49 XG-SB 0.20	Formula	PANTONE 7493 C XG-TW 90.43 XG-064 7.55 XG-127 1.60 XG-230 0.42	Formula	PANTONE 7494 C XG-TW 84.22 XG-SB 9.38 XG-064 5.84 XG-230 0.56	Formula	PANTONE 7495 C XG-064 38.42 XG-MX 20.00 XG-TW 27.71 XG-SB 13.14 XG-230 0.73	Formula
PANTONE 7496 C XG-064 76.92 XG-TW 13.98 XG-230 4.23 XG-114 2.51 XG-121 2.36	Formula	PANTONE 7497 C XG-TW 52.93 XG-SB 34.37 XG-064 10.96 XG-114 1.74	Formula	PANTONE 7498 C XG-064 44.02 XG-SB 35.92 XG-TW 12.35 XG-165 5.69 XG-230 2.02	Formula	PANTONE 7499 C XG-TW 99.14 XG-066 0.62 XG-127 0.24	Formula
PANTONE 7500 C XG-TW 95.52 XG-064 2.58 XG-SB 1.68 XG-164 0.22	Formula	PANTONE 7501 C XG-TW 77.34 XG-MX 20.00 XG-066 1.42 XG-127 1.24	Formula	PANTONE 7502 C XG-TW 86.23 XG-064 6.99 XG-MX 4.30 XG-127 2.01 XG-114 0.47	Formula	PANTONE 7503 C XG-TW 71.35 XG-064 22.96 XG-127 5.69	Formula

Plastijet XG

PANTONE 7504 C XG-TW 58.20 XG-064 27.99 XG-127 7.19 XG-SB 4.63 XG-164 1.99	Formula	PANTONE 7505 C XG-TW 37.20 XG-SB 29.79 XG-064 21.86 XG-114 6.27 XG-165 4.88	Formula	PANTONE 7506 C XG-TW 97.60 XG-064 2.04 XG-164 0.36	Formula	PANTONE 7507 C XG-TW 96.57 XG-066 1.80 XG-121 1.63	Formula
PANTONE 7508 C XG-TW 90.22 XG-064 7.32 XG-127 1.29 XG-114 1.17	Formula	PANTONE 7509 C XG-TW 85.98 XG-066 6.81 XG-165 3.74 XG-SB 3.47	Formula	PANTONE 7510 C XG-TW 73.39 XG-066 18.72 XG-121 6.74 XG-230 0.95 XG-114 0.20	Formula	PANTONE 7511 C XG-064 62.09 XG-TW 21.59 XG-SB 10.15 XG-114 4.91 XG-164 1.26	Formula
PANTONE 7512 C XG-064 67.88 XG-SB 14.85 XG-TW 6.57 XG-114 5.86 XG-121 4.84	Formula	PANTONE 7513 C XG-TW 98.24 XG-114 1.01 XG-164 0.50 XG-230 0.25	Formula	PANTONE 7514 C XG-TW 90.26 XG-SB 4.28 XG-121 3.48 XG-066 1.98	Formula	PANTONE 7515 C XG-TW 80.75 XG-SB 7.97 XG-064 4.90 XG-121 3.32 XG-114 3.06	Formula
PANTONE 7516 C XG-TW 45.27 XG-SB 19.98 XG-066 17.80 XG-114 14.59 XG-164 2.36	Formula	PANTONE 7517 C XG-066 28.80 XG-SB 28.45 XG-TW 23.00 XG-121 10.58 XG-114 9.17	Formula	PANTONE 7518 C XG-SB 36.60 XG-TW 23.91 XG-MX 20.00 XG-165 15.31 XG-066 4.18	Formula	PANTONE 7519 C XG-SB 52.17 XG-TW 34.27 XG-066 9.35 XG-164 4.21	Formula

Plastijet XG

PANTONE 7520 C XG-TW 98.32 XG-114 0.92 XG-164 0.58 XG-230 0.18	Formula	PANTONE 7521 C XG-TW 84.04 XG-064 8.56 XG-165 4.75 XG-127 2.65	Formula	PANTONE 7522 C XG-TW 51.96 XG-064 20.74 XG-165 19.94 XG-SB 7.36	Formula	PANTONE 7523 C XG-TW 62.82 XG-121 20.78 XG-SB 13.16 XG-066 3.24	Formula
PANTONE 7524 C XG-TW 57.16 XG-121 33.73 XG-066 7.23 XG-230 1.88	Formula	PANTONE 7525 C XG-TW 48.48 XG-064 31.21 XG-SB 14.64 XG-164 5.67	Formula	PANTONE 7526 C XG-SB 24.18 XG-TW 22.68 XG-066 22.38 XG-114 17.40 XG-121 13.36	Formula	PANTONE 7527 C XG-TW 76.68 XG-MX 20.00 XG-SB 3.27 XG-064 0.05	Formula
PANTONE 7528 C XG-TW 74.06 XG-MX 20.00 XG-SB 5.61 XG-114 0.17 XG-164 0.16	Formula	PANTONE 7529 C XG-TW 88.95 XG-SB 9.48 XG-165 0.71 XG-114 0.47 XG-064 0.39	Formula	PANTONE 7530 C XG-TW 80.65 XG-SB 14.02 XG-064 2.85 XG-121 2.48	Formula	PANTONE 7531 C XG-TW 64.80 XG-SB 17.98 XG-066 7.21 XG-127 6.42 XG-121 3.59	Formula
PANTONE 7532 C XG-SB 45.37 XG-TW 28.32 XG-MX 20.00 XG-114 4.77 XG-064 1.54	Formula	PANTONE 7533 C XG-SB 81.00 XG-MX 14.03 XG-114 4.97	Formula	PANTONE 7534 C XG-TW 76.40 XG-MX 20.00 XG-SB 3.57 XG-066 0.03	Formula	PANTONE 7535 C XG-TW 95.12 XG-127 2.79 XG-066 1.68 XG-325 0.41	Formula

Plastijet XG

PANTONE 7536 C XG-TW 91.90 XG-127 4.32 XG-066 3.13 XG-325 0.65	Formula	PANTONE 7537 C XG-TW 69.93 XG-MX 20.00 XG-SB 9.57 XG-064 0.33 XG-230 0.17	Formula	PANTONE 7538 C XG-TW 84.50 XG-SB 14.74 XG-064 0.54 XG-230 0.22	Formula	PANTONE 7539 C XG-TW 89.30 XG-127 6.47 XG-066 2.87 XG-325 1.36	Formula
PANTONE 7540 C XG-SB 46.57 XG-TW 37.62 XG-165 11.43 XG-325 4.38	Formula	PANTONE 7541 C XG-TW 99.20 XG-127 0.57 XG-230 0.23	Formula	PANTONE 7542 C XG-TW 94.38 XG-SB 4.03 XG-230 0.81 XG-165 0.78	Formula	PANTONE 7543 C XG-TW 89.91 XG-SB 7.24 XG-165 2.00 XG-230 0.85	Formula
PANTONE 7544 C XG-TW 64.07 XG-MX 20.00 XG-SB 13.34 XG-230 1.57 XG-164 1.02	Formula	PANTONE 7545 C XG-TW 37.37 XG-SB 34.93 XG-MX 20.00 XG-230 5.09 XG-164 2.61	Formula	PANTONE 7546 C XG-SB 59.31 XG-MX 20.00 XG-165 14.87 XG-230 5.82	Formula	PANTONE 7547 C XG-SB 84.95 XG-325 7.00 XG-127 8.05	Formula