

[View Translatable Version](#)

Description	WV1105 ROP-DE Coating was developed for Moisture Res, Thermal Transfer Ribbons (Wax/Resin), Direct Thermal, and High Rub properties.														
Substrates	Paper stock and Films														
Properties	<table border="0"> <tr> <td style="padding-right: 20px;">Target Viscosity</td> <td>25-30sec/#2 Zahn @ 70°F</td> </tr> <tr> <td>Resistance</td> <td>Water and Alkali</td> </tr> <tr> <td>pH</td> <td>8.5-9.5</td> </tr> <tr> <td>VOC</td> <td><0.05</td> </tr> <tr> <td>Other</td> <td>FDA: Dry Film-21 CFR: 175.170, 176.170 (with Limits), and 176.180</td> </tr> <tr> <td>Drying</td> <td>Sufficient volumes of warm air, medium or short wave I.R.</td> </tr> <tr> <td>Shelf Life</td> <td>6 months (Unopened containers)</td> </tr> </table>	Target Viscosity	25-30sec/#2 Zahn @ 70°F	Resistance	Water and Alkali	pH	8.5-9.5	VOC	<0.05	Other	FDA: Dry Film-21 CFR: 175.170, 176.170 (with Limits), and 176.180	Drying	Sufficient volumes of warm air, medium or short wave I.R.	Shelf Life	6 months (Unopened containers)
Target Viscosity	25-30sec/#2 Zahn @ 70°F														
Resistance	Water and Alkali														
pH	8.5-9.5														
VOC	<0.05														
Other	FDA: Dry Film-21 CFR: 175.170, 176.170 (with Limits), and 176.180														
Drying	Sufficient volumes of warm air, medium or short wave I.R.														
Shelf Life	6 months (Unopened containers)														
Application Suggestions	<p>It is recommended that you use an anilox that will apply a wet ink film weight of 0.8-1.2 lbs/MSF to optimize coating performance.</p> <p>This product is formulated to be press ready and can be printed over Nazdar® Rotary Screen, UV Flexo and Water Base Flexo i</p>														
Performance Verification	After press/job set up is complete, inspect a portion of the printed web for all applicable and specified properties. These properties include but are not limited to: cure, adhesion, mar and rub resistance, product resistance, gloss, and coefficient of friction. These tests should be performed prior to beginning the full production run.														
Clean Up	Use NWC10 EZ Cleaner.														
Storage and Handling	<p>Proper personal protection equipment and adequate ventilation are required when handling this material. Please consult MSDS for details on proper handling of this material. This product should be stored tightly covered at temperatures between 65° - 90°F (18° - 32°C).</p> <p>The product should be mixed prior to use.</p>														

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

Nazdar - World Headquarters

8501 Hedge Lane Terrace, Shawnee, KS 66227-3290 USA
 Toll Free US: +1 866.340.3579
 Tel: +1 913 422 1888
 E-mail: NazdarOrders@nazdar.com
 Technical Service Email: InkAnswers@Nazdar.com

Nazdar Limited - EMEA

Barton Road, Heaton Mersey, Stockport, England SK4 3EG
 Tel: +44 161 442 2111
 Technical Service Email: technicalservicesuk@nazdar.com